

CENTRAL ENVIRONMENTAL INC.

91 McClellan Street, Bronx, NY 10452
Tel: (718) 293-8727; Fax: (718) 992-4300

ASBESTOS AIRBORNE PERMISSIBLE EXPOSURE LEVELS (PEL).
Adopted by various Governmental Agencies.

AGENCY LEVELS	ASBESTOS CONCENTRATION
Occupational Safety & Safety Health Administration.	0.1 fibers/cc
National Institute for Occupational Safety & Health.	0.1 fibers/cc
Department of Environmental Protection New York City.	0.01 fiber/cc
Environmental Protection Agency (After Asbestos Removal).	0.01 fibers/cc

CENTRAL ENVIRONMENTAL, INC.

91 McClellan Street, Bronx, New York 10452

Tel: (718) 293-8727 Fax: (718) 992-4300

September 25, 2001

SCHLANG BROS. & CO., INC.
67 Wall Street
New York, NY 10005

Attn: Vincent Castagna:

Re: Samples taken at 67 Wall Street, New York, NY10005


Central Environmental, Inc. performed Asbestos Dust Wipe Test on various floor mainly common hallways.

The purpose of this test was to determine the presence or absence of (ACM) asbestos containing material in dust wipes.

Thirty eight samples were sampled from windows, doors, elevator banks, etc on various floors. The samples were then analyzed by POLARIZED light microscopy following EPA-600/M4-020.

The results were all negative. See attached copies.

Sincerely,

A handwritten signature in black ink, appearing to read 'Alim Yerima', with a stylized flourish at the end.

Alim Yerima.

ENVIRO-PROBE, INC.
2917 Bruckner Boulevard - Bronx, New York 10461
Phone: (718) 863-0045 - Fax: (718) 518-7454

BULK MATERIAL ANALYSIS FOR ASBESTOS

TEST METHOD - POLARIZED LIGHT MICROSCOPY - EPA/600/R-93/116, July 1993
NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM LAB ID# 101222
NEW YORK STATE ENVIRONMENTAL LABORATORY APPROVAL PROGRAM LAB ID# 10898

CLIENT NAME Central Env. Services
COMPANY
ADDRESS
CITY, STATE, ZIP

DATE SUBMITTED: 9/24/01
DATE ANALYZED: 9/24/01
DATE REPORTED: 9/26/01
LAB FILE # 23312
ANALYST S. K. Dewan

1. SAMPLING LOCATION	67/69 Wall St., NY. Various Floors					
2. CLIENT'S ID#	1	2	3	4	5	6
3. LAB ID# B01-	20273	20274	20275	20276	20277	20278
4. STEREO-MICROSCOPIC EXAMINATION						
1. HOMOGENEOUS (Y/N)	N	N	N	N	N	N
2. COLOR	1 & 4	1 & 4	1 & 4	1 & 4	1 & 4	1 & 4
1. WHITE						
2. BROWN						
3. GRAY						
4. OTHERS						
5. ASBESTOS DETECTED (YES/NO)	N	N	N	N	N	N
6. ASBESTOS PERCENTAGE						
1. AMOSITE						
2. CHRYSOTILE						
3. CROCIDOLITE						
4. OTHERS						
7. TOTAL ASBESTOS PERCENTAGE	0	0	0	0	0	0
8. PERCENTAGE - OTHER FIBROUS MATERIALS						
1. CELLULOSE						
2. FIBROUS GLASS	10	10	40	10	15	20
3. OTHERS	20	25	20	25	20	25
9. NON-FIBROUS MATERIALS						
1. CARBONATES	15	20	15	15	15	20
2. SILICATES	15	15	15	20	15	20
3. OTHERS	40	30	10	30	35	15
10. TOTAL	100	100	100	100	100	100

This report shall not be reproduced except in full, without the written approval of the laboratory.

For quantitation purposes 1% is the concentration at which there is an uncertainty

.. These results apply to these/this particular samples/sample

o This report is not endorsed by NVLAP or any other U.S. Government Agency

..... Traces = < 1%


LAB DIRECTOR/SUPERVISOR'S SIGNATURE

ENVIRO-PROBE, INC.
2917 Bruckner Boulevard - Bronx, New York 10461
Phone: (718) 863-0045 - Fax: (718) 518-7454

BULK MATERIAL ANALYSIS FOR ASBESTOS

TEST METHOD - POLARIZED LIGHT MICROSCOPY - EPA/600/R-93/116, July 1993
NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM LAB ID# 101222
NEW YORK STATE ENVIRONMENTAL LABORATORY APPROVAL PROGRAM LAB ID# 10898

CLIENT NAME Central Env. Services
COMPANY
ADDRESS
CITY, STATE, ZIP

DATE SUBMITTED: 9/24/01
DATE ANALYZED: 9/24/01
DATE REPORTED: 9/26/01
LAB FILE # 23312
ANALYST S. K. Dewan

1. SAMPLING LOCATION	67/69 Wall St., NY. Various Floors					
2. CLIENT'S ID#	7	8	9	10	11	12
3. LAB ID# B01-	20279	20280	20281	20282	20283	20284
4. STEREO-MICROSCOPIC EXAMINATION						
1. HOMOGENEOUS (Y/N)	N	N	N	N	N	N
2. COLOR	1 & 4	1 & 4	1 & 4	1 & 4	1 & 4	1 & 4
1. WHITE						
2. BROWN						
3. GRAY						
4. OTHERS						
5. ASBESTOS DETECTED (YES/NO)	N	N	N	N	N	N
6. ASBESTOS PERCENTAGE						
1. AMOSITE						
2. CHRYSOTILE						
3. CROCIDOLITE						
4. OTHERS						
7. TOTAL ASBESTOS PERCENTAGE	0	0	0	0	0	0
8. PERCENTAGE - OTHER FIBROUS MATERIALS						
1. CELLULOSE						
2. FIBROUS GLASS	40	30	20	20	15	25
3. OTHERS	20	15	20	35	30	20
9. NON-FIBROUS MATERIALS						
1. CARBONATES	15	15	15	20	15	20
2. SILICATES	10	15	10	15	10	10
3. OTHERS	15	25	35	10	30	25
10. TOTAL	100	100	100	100	100	100

This report shall not be reproduced except in full, without the written approval of the laboratory.

For quantitation purposes 1% is the concentration at which there is an uncertainty

.. These results apply to these/these particular samples/sample

o This report is not endorsed by NVLAP or any other U.S. Government Agency

..... Traces = < 1%


LAB DIRECTOR/SUPERVISOR'S SIGNATURE

ENVIRO-PROBE, INC.
2917 Bruckner Boulevard - Bronx, New York 10461
Phone: (718) 863-0045 - Fax: (718) 518-7454

BULK MATERIAL ANALYSIS FOR ASBESTOS

TEST METHOD - POLARIZED LIGHT MICROSCOPY - EPA/600/R-93/116, July 1993
NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM LAB ID# 101222
NEW YORK STATE ENVIRONMENTAL LABORATORY APPROVAL PROGRAM LAB ID# 10898

CLIENT NAME Central Env. Services
COMPANY
ADDRESS
CITY,STATE, ZIP

DATE SUBMITTED: 9/24/01
DATE ANALYZED: 9/24/01
DATE REPORTED: 9/26/01
LAB FILE # 23312
ANALYST S. K. Dewan

1. SAMPLING LOCATION	67/69 Wall St., NY. Various Floors					
2. CLIENT'S ID#	13	14	15	16	17	18
3. LAB ID# B01-	20285	20286	20287	20288	20289	20290
4. STEREO-MICROSCOPIC EXAMINATION						
1. HOMOGENEOUS (Y/N)	N	N	N	N	N	N
2. COLOR	1 & 4	1 & 4	1 & 4	1 & 4	1 & 4	1 & 4
1. WHITE						
2. BROWN						
3. GRAY						
4. OTHERS						
5. ASBESTOS DETECTED (YES/NO)	N	N	N	N	N	N
6. ASBESTOS PERCENTAGE						
1. AMOSITE						
2. CHRYSOTILE						
3. CROCIDOLITE						
4. OTHERS						
7. TOTAL ASBESTOS PERCENTAGE	0	0	0	0	0	0
8. PERCENTAGE - OTHER FIBROUS MATERIALS						
1. CELLULOSE						
2. FIBROUS GLASS	35	20	15	25	25	20
3. OTHERS	15	20	25	15	15	20
9. NON-FIBROUS MATERIALS						
1. CARBONATES	15	10	15	15	20	10
2. SILICATES	10	15	10	10	15	10
3. OTHERS	25	35	35	35	25	40
10. TOTAL	100	100	100	100	100	100

This report shall not be reproduced except in full, without the written approval of the laboratory.

For quantitation purposes 1% is the concentration at which there is an uncertainty

.. These results apply to these/this particular samples/sample

o This report is not endorsed by NVLAP or any other U.S. Government Agency

.... Traces = < 1%


LAB DIRECTOR/SUPERVISOR'S SIGNATURE

ENVIRO-PROBE, INC.**2917 Bruckner Boulevard - Bronx, New York 10461****Phone: (718) 863-0045 - Fax: (718) 518-7454****BULK MATERIAL ANALYSIS FOR ASBESTOS**

TEST METHOD - POLARIZED LIGHT MICROSCOPY - EPA/600/R-93/116, July 1993
NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM LAB ID# 101222
NEW YORK STATE ENVIRONMENTAL LABORATORY APPROVAL PROGRAM LAB ID# 10898

CLIENT NAME Central Env. Services
COMPANY
ADDRESS
CITY, STATE, ZIP

DATE SUBMITTED: 9/24/01
DATE ANALYZED: 9/24/01
DATE REPORTED: 9/26/01
LAB FILE # 23312
ANALYST S. K. Dewan

1. SAMPLING LOCATION	67/69 Wall St., NY. Various Floors					
2. CLIENT'S ID#	19	20	21	22	23	24
3. LAB ID# B01-	20291	20292	20293	20294	20295	20296
4. STEREO-MICROSCOPIC EXAMINATION						
1. HOMOGENEOUS (Y/N)	N	N	N	N	N	N
2. COLOR	1 & 4	1 & 4	1 & 4	1 & 4	1 & 4	1 & 4
1. WHITE						
2. BROWN						
3. GRAY						
4. OTHERS						
5. ASBESTOS DETECTED (YES/NO)	N	N	N	N	N	N
6. ASBESTOS PERCENTAGE						
1. AMOSITE						
2. CHRYSOTILE						
3. CROCIDOLITE						
4. OTHERS						
7. TOTAL ASBESTOS PERCENTAGE	0	0	0	0	0	0
8. PERCENTAGE - OTHER FIBROUS MATERIALS						
1. CELLULOSE						
2. FIBROUS GLASS	25	30	15	20	20	25
3. OTHERS	15	15	20	25	20	15
9. NON-FIBROUS MATERIALS						
1. CARBONATES	15	20	15	15	20	10
2. SILICATES	10	10	15	10	10	15
3. OTHERS	35	25	35	30	30	35
10. TOTAL	100	100	100	100	100	100

This report shall not be reproduced except in full, without the written approval of the laboratory.

For quantitation purposes 1% is the concentration at which there is an uncertainty

.. These results apply to these/these particular samples/sample

o This report is not endorsed by NVLAP or any other U.S. Government Agency

..... Traces = < 1%

LAB DIRECTOR/SUPERVISOR'S SIGNATURE

ENVIRO-PROBE, INC.
2917 Bruckner Boulevard - Bronx, New York 10461
Phone: (718) 863-0045 - Fax: (718) 518-7454

BULK MATERIAL ANALYSIS FOR ASBESTOS

TEST METHOD - POLARIZED LIGHT MICROSCOPY - EPA/600/R-93/116, July 1993
NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM LAB ID# 101222
NEW YORK STATE ENVIRONMENTAL LABORATORY APPROVAL PROGRAM LAB ID# 10898

CLIENT NAME Central Env. Services
COMPANY
ADDRESS
CITY, STATE, ZIP

DATE SUBMITTED: 9/24/01
DATE ANALYZED: 9/24/01
DATE REPORTED: 9/26/01
LAB FILE # 23312
ANALYST S. K. Dewan

1. SAMPLING LOCATION	67/69 Wall St., NY. Various Floors					
2. CLIENT'S ID#	25	26	27	28	29	30
3. LAB ID#	B01- 20297	20298	20299	20300	20301	20302
4. STEREO-MICROSCOPIC EXAMINATION	N 1 & 4	N 1 & 4	N 1 & 4	N 1 & 4	N 1 & 4	N 1 & 4
1. HOMOGENEOUS (Y/N)						
2. COLOR						
1. WHITE						
2. BROWN						
3. GRAY						
4. OTHERS						
5. ASBESTOS DETECTED (YES/NO)	N	N	N	N	N	N
6. ASBESTOS PERCENTAGE						
1. AMOSITE						
2. CHRYSOTILE						
3. CROCIDOLITE						
4. OTHERS						
7. TOTAL ASBESTOS PERCENTAGE	0	0	0	0	0	0
8. PERCENTAGE - OTHER FIBROUS MATERIALS						
1. CELLULOSE						
2. FIBROUS GLASS	35	15	30	20	15	20
3. OTHERS	15	20	15	25	25	20
9. NON-FIBROUS MATERIALS						
1. CARBONATES	10	15	15	10	20	15
2. SILICATES	10	15	10	10	15	10
3. OTHERS	30	35	30	35	25	35
10. TOTAL	100	100	100	100	100	100

This report shall not be reproduced except in full, without the written approval of the laboratory.

For quantitation purposes 1% is the concentration at which there is an uncertainty

.. These results apply to these/these particular samples/sample

o This report is not endorsed by NVLAP or any other U.S. Government Agency

..... Traces = < 1%


 LAB DIRECTOR/SUPERVISOR'S SIGNATURE

ENVIRO-PROBE, INC.**2917 Bruckner Boulevard - Bronx, New York 10461****Phone: (718) 863-0045 - Fax: (718) 518-7454****BULK MATERIAL ANALYSIS FOR ASBESTOS**

TEST METHOD - POLARIZED LIGHT MICROSCOPY - EPA/600/R-93/116, July 1993
NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM LAB ID# 101222
NEW YORK STATE ENVIRONMENTAL LABORATORY APPROVAL PROGRAM LAB ID# 10898

CLIENT NAME Central Env. Services
COMPANY
ADDRESS
CITY,STATE, ZIP

DATE SUBMITTED: 9/24/01
DATE ANALYZED: 9/24/01
DATE REPORTED: 9/26/01
LAB FILE # 23312
ANALYST S. K. Dewan

1. SAMPLING LOCATION	67/69 Wall St., NY. Various Floors					
2. CLIENT'S ID#	31	32	33	34	35	36
3. LAB ID# B01-	20303	20304	20305	20306	20307	20308
4. STEREO-MICROSCOPIC EXAMINATION						
1. HOMOGENEOUS (Y/N)	N	N	N	N	N	N
2. COLOR	1 & 4	1 & 4	1 & 4	1 & 4	1 & 4	1 & 4
1. WHITE						
2. BROWN						
3. GRAY						
4. OTHERS						
5. ASBESTOS DETECTED (YES/NO)	N	N	N	N	N	N
6. ASBESTOS PERCENTAGE						
1. AMOSITE						
2. CHRYSOTILE						
3. CROCIDOLITE						
4. OTHERS						
7. TOTAL ASBESTOS PERCENTAGE	0	0	0	0	0	0
8. PERCENTAGE - OTHER FIBROUS MATERIALS						
1. CELLULOSE						
2. FIBROUS GLASS	20	25	15	15	30	20
3. OTHERS	15	15	25	20	15	20
9. NON-FIBROUS MATERIALS						
1. CARBONATES	15	15	20	25	15	20
2. SILICATES	10	15	10	10	10	10
3. OTHERS	40	30	30	30	30	30
10. TOTAL	100	100	100	100	100	100

This report shall not be reproduced except in full, without the written approval of the laboratory.

For quantitation purposes 1% is the concentration at which there is an uncertainty

... These results apply to these/these particular samples/sample

o This report is not endorsed by NVLAP or any other U.S. Government Agency

..... Traces = < 1%

LAB DIRECTOR/SUPERVISOR'S SIGNATURE

ENVIRO-PROBE, INC.

2917 Bruckner Boulevard - Bronx, New York 10461
Phone: (718) 863-0045 - Fax: (718) 518-7454

BULK MATERIAL ANALYSIS FOR ASBESTOS

TEST METHOD - POLARIZED LIGHT MICROSCOPY - EPA/600/R-93/116, July 1993
NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM LAB ID# 101222
NEW YORK STATE ENVIRONMENTAL LABORATORY APPROVAL PROGRAM LAB ID# 10898

CLIENT NAME Central Env. Services
COMPANY
ADDRESS
CITY, STATE, ZIP

DATE SUBMITTED: 9/24/01
DATE ANALYZED: 9/24/01
DATE REPORTED: 9/26/01
LAB FILE # 23312
ANALYST S. K. Dewan

1. SAMPLING LOCATION	67/69 Wall St., NY. Various Floors					
2. CLIENT'S ID#	37	38				
3. LAB ID#	B01-	20309	20310			
4. STEREO-MICROSCOPIC EXAMINATION						
1. HOMOGENEOUS (Y/N)	N	N				
2. COLOR	1 & 4	1 & 4				
1. WHITE						
2. BROWN						
3. GRAY						
4. OTHERS						
5. ASBESTOS DETECTED (YES/NO)	N	N				
6. ASBESTOS PERCENTAGE						
1. AMOSITE						
2. CHRYSOTILE						
3. CROCIDOLITE						
4. OTHERS						
7. TOTAL ASBESTOS PERCENTAGE	0	0				
8. PERCENTAGE - OTHER FIBROUS MATERIALS						
1. CELLULOSE						
2. FIBROUS GLASS	15	20				
3. OTHERS	30	25				
9. NON-FIBROUS MATERIALS						
1. CARBONATES	15	15				
2. SILICATES	10	15				
3. OTHERS	30	25				
10. TOTAL	100	100				

This report shall not be reproduced except in full, without the written approval of the laboratory.

For quantitation purposes 1% is the concentration at which there is an uncertainty

.. These results apply to these/these particular samples/sample

o This report is not endorsed by NVLAP or any other U.S. Government Agency

..... Traces = < 1%

LAB DIRECTOR/SUPERVISOR'S SIGNATURE

Address: 67 WALL ST.

Bulk Samples ☒ Yes No
PLM

Number of Negative ($\leq 1\%$) Samples 30

Number of Positive ($> 1\%$) Samples 0

Air Samples ☒ Yes No

PCM Number of Samples Collected ($\leq 0.01\text{f/cc}$) 30

Number of Samples Collected ($>0.01\text{ f/cc}$) 0

TEM Number of Samples Collected ($\leq 70\text{ s/mm}^2$) _____

Number of Samples Collected ($>70\text{ s/mm}^2$) _____