

CON-LUX® MATERIAL SAFETY DATA

PAGE 1

SECTION I

DATE: 06/23/92

MANUFACTURER'S NAME: CON-LUX Coatings, Inc.

STREET ADDRESS: 226 Talmadge Rd. Edison, NJ 08818-0847

EMERGENCY TELEPHONE NOs:

Monday-Friday / 8:30am - 5:00pm: 908-287-4000

Off hours, Weekends, & Holidays: CHEMTREC 800-424-9300

PRODUCT CLASS: ALKYD ENAMEL

TRADE NAME: ENAMELITE 548 JET BLACK

SECTION II - HAZARDOUS INGREDIENTS

INGREDIENTS	! % ! ! BY ! ! WT !	OEL	! LEL !	! VAPOR ! ! mmHg @ ! 20C !
CARBON BLACK	!>1% !	!3.5 mg/m3 !	! !	! 0.00 !
CAS NO. 1333-86-4	! !	!ACGIH-TLV !	! !	! !
METHYL iso-AMYL KETONE	!>1% !	!50ppm ACGIH-TLV !	!2.7 !	! 4.00 !
CAS NO. 110-12-3	! !	!50ppm OSHA-PEL !	! !	! !
MINERAL SPIRITS	!>1% !	!100ppm OSHA-PEL !	!1.0 !	! 2.00 !
CAS NO. 8052-41-3	! !	!100ppm ACGIH-TLV !	! !	! !
AROMATIC NAPHTHA	!>1% !	!100ppm OSHA-PEL !	!1.0 !	! 3.00 !
CAS NO. 64742-95-6	! !	! !	! !	! !

* Material Regulated Under SARA Title III, Section 313

SECTION III - PHYSICAL DATA

BOILING RANGE: 210 - 500F

EVAPORATION RATE: SLOWER THAN ETHER

VAPOR DENSITY: HEAVIER THAN AIR

% VOLATILE

WEIGHT PER

BY VOLUME: 42.95

GALLON 8.00