NYC 9/11 Public Portal Document

# ATC ASSOCIATES INC. – TEM ANALYSIS

LAB GROUP #: 5579 - 09/29/01

Lab Sample No. 59742 | Filter Type MCE 25 mm | Operator WCP

Client Spl. No. T19 | Filter Area 385 mm^2

Instrument I.D. EM 10 CRX | Grid I.D. 423 | Disk No.

Screen Magnification 16,400X | (GO) Area 0.01124 mm^2 | Comments

Acc. Voltage 80 kV | No. GO to be Analyzed 6 | ( 4.721 Struct. Corspd. to 70 s/mm^2.)

| GO. No. | GO. Coord. | Structure No. | Structure Type F | B | C | M | Length ≥0.5 um < 5 um | Length ≥ 5um | I.D. of Structure Chrys. | Amphibole | Nonasb. | N or ✓ Ambig./ND | EDS (Nonasb. Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 | E2 | MS2 | | | | | | | | | | | |
| 2 | J2 | — " — | | | | | | | | | | | |
| 3 | Q2 | — " — | | | | | | | | | | | |
| 4 | F2 | — " — | | | | | | | | | | | |
| 5 | K2 | — " — | | | | | | | | | | | |
| 6 | R2 | — " — | | | | | | | | | | | |

Photo No. (from 1 in 5 asbestos-containing samples)

Identify all structures using EDS

Check diffraction for asbestos structures up to 70s/mm (1st 4)

Store all unrepeated spectra

Struct. = ≥ 0.5um & > 5:1 Aspect Ratio

N= Not Observed (EDS spectrum or diffraction pattern)

✓= Positive diffraction pattern properties conforming to laboratory identification criteria observed.

For chrysotile: 0.73nm spacing for (020) reflections, 0.53nm spacing for the layer line repeat, streaking of (110) and (130) reflections.


For amphiboles: 0.53nm layer line repeat, and approx. 3.5 ratio of non-twinned layer line spot spacing to layer line repeat distance (0.53nm).

✓= EDS spectrum conforming to laboratory identification criteria observed.

F= Single Fiber (1-3 intersections = 1-3 fibers)
B= Bundle (>3 fibers <1 fiber diameter apart)
C= Cluster (>3 intersections)
M= Matrix
NSD= No Structures Detected

L:\DATA\PRIVATE\MIKEG\CADD\TEM3 9/22/98

Grid acceptance:
<50% undissolved filter, overlapped or folded
<10% particulate coverage >50% coverage
at least 20 unfolded or overlapped grid squares
<5% holes or opaque areas




Stopping Rules:
>50 s/G.O. or in 1st 4 G.O.

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

Totals

| | F | B | C | M | ≥ 5um |
|---|---|---|---|---|---|
| Chrysotile | | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-asbestos | | | | | |
| Non-Identified | | | | | |

NYC-WTC_000174854