

New York Lab

307 West 38th Street, New York, NY 10018

Phone: 212-290-0051 Fax: 212-290-0058 Email:

EMSL

Attn: U. S. EPA
 HQ Financial Services Division
 1200 Pennsylvania Ave. NW Maildrop 2734R
 Washington, DC 20460

Fax: Phone:

Project: USPHS Mission #12: Residential Sampling New York
 City-258 Broadway / Bldg. 4

Customer ID: USEPA30
 Customer PO: 2W-1104-NNLX
 Received: 11/15/01 7:12 PM

EMSL Order: 030108084
 EMSL Project ID:


Analysis Date: 11/17/01

Asbestos Analysis of Bulk Materials by PLM via the NY State ELAP 198.1 Method

Sample	Location	Appearance	Treatment	Non-Asbestos		Asbestos
				% Fibrous	% Non-Fibrous	% Type
[R]VA-C-4 030108084-0001	Common Area	Gray Fibrous Heterogeneous	Teased	15.00% Glass 3.00% Cellulose	10.00% Quartz 72.00% Non-fibrous (other)	None Detected
[R]VA-R1-4 030108084-0002	Residence 1	Gray Fibrous Heterogeneous	Teased	2.00% Glass 10.00% Cellulose	20.00% Quartz 68.00% Non-fibrous (other)	None Detected
[R]VA-R2-4 030108084-0003	Residence 2	Gray Fibrous Heterogeneous	Teased	5.00% Hair 5.00% Glass 25.00% Cellulose	10.00% Quartz 55.00% Non-fibrous (other)	None Detected

Alex Chechelovskij

Analyst



Laboratory Manager
 or other approved signatory

PLM has been known to miss asbestos in a small percentage of samples which contain asbestos. Negative PLM results cannot be guaranteed. Samples reported as <1% or none detected should be tested with TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical, Inc. The above test must not be used by the client to claim product endorsement by NVLAP nor any agency of the United States Government.

Analysis performed by EMSL Manhattan (NVLAP #101048-9), NY ELAP 11508

PLM P/Int Count-1

1

CONFIDENTIAL,

CITY_21MC100_003423572

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008