

New York Lab

107 West 38th Street, New York, NY 10018

Phone: 212-290-0051 Fax: 212-290-0058 Email:

EMSL

Attn: Emteque Corporation
505 Eighth Avenue
Suite 900
New York, NY 10018

Fax: (212) 631-8066 Phone: 212-631-9000

Project: 010496 90 Church Street

Customer ID: EMT51
Customer PO:
Received: 10/13/01 5:00 PM

EMSL Order: 030106235
EMSL Project ID:


Analysis Date: 10/15/01

Asbestos Analysis of Bulk Materials by PLM via the NY State ELAP 198.1 Method

Sample	Location	Appearance	Treatment	Non-Asbestos		Asbestos
				% Fibrous	% Non-Fibrous	% Type
A6-04 30106235-0011	SE corner window ledge office 6480	Gray Fibrous Heterogeneous	Dissolved Teased	48.00% Glass 32.00% Cellulose	20.00% Non-fibrous (other)	<1% Chrysotile
A6-05 30106235-0012	E side cafeteria carpet floor	Gray Fibrous Heterogeneous	Dissolved Teased	48.00% Glass 22.00% Cellulose	28.00% Non-fibrous (other)	2.00% Chrysotile
A6-06 030106235-0013	N side window sill adj 6147	Gray Fibrous Heterogeneous	Dissolved Teased	45.00% Glass 35.00% Cellulose	20.00% Non-fibrous (other)	None Detected
A6-07 6235-0014	NW corner window sill adj 6244	Gray Fibrous Heterogeneous	Dissolved Teased	45.00% Glass 30.00% Cellulose	25.00% Non-fibrous (other)	None Detected
A6-08 030106235-0015	WN side window sill adj 6245	Gray Fibrous Heterogeneous	Dissolved Teased	45.00% Glass 35.00% Cellulose	20.00% Non-fibrous (other)	None Detected
A6-09 30106235-0016	Central area reception counter	Beige Fibrous Homogeneous	Crushed Teased	65.00% Cellulose	35.00% Non-fibrous (other)	None Detected
A7-01 30106235-0017	N side assist director office window sill	Gray Fibrous Heterogeneous	Dissolved Teased	45.00% Glass 35.00% Cellulose	20.00% Non-fibrous (other)	None Detected
A7-02 30106235-0018	N side bldg services & receiving room	Gray Fibrous Heterogeneous	Dissolved Teased	45.00% Glass 30.00% Cellulose	25.00% Non-fibrous (other)	None Detected
A7-03 30106235-0019	NW side mall room window sill	Gray Fibrous Heterogeneous	Dissolved Teased	48.00% Glass 30.00% Cellulose	22.00% Non-fibrous (other)	<1% Chrysotile
A5-01 030106235-0020	SW corner office 5377	Gray Fibrous Heterogeneous	Dissolved Teased	60.00% Glass 22.00% Cellulose	18.00% Non-fibrous (other)	<1% Chrysotile

Ram Yallabandi

Analyst



Laboratory Manager
or other approved signatory

It has been known to miss asbestos in a small percentage of samples which contain asbestos. Negative PLM results cannot be guaranteed. Samples reported as <1% or none selected should be tested with TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical, Inc. The above test must not be used by the client to claim product endorsement by NVLAP nor any agency of the United States Government.

Analysis performed by EMSL Manhattan (NVLAP #101048-9), NY ELAP 11506

PLM Print Count-1

2