

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

104 East 25th Street, 10th Floor - New York, NY 10010 - Phone (212) 353 - 8280, FAX (212) 353 - 3599 or 8306

NVLAP 101187

ELAP 10879

Microscope OLYMP BH-2

Client / Project NYC-BOE/PS 89M, 201 WARREN ST. NY, NY 10282Project No. 14584-0819Analysis Date 04/26/02 Analyst E. A. GUANTEROSBatch No. 20315

Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
01	Color <u>Brown</u> Texture <u>Gr.</u>	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>100</u> Fiberglass _____ Other _____	Mineral Filler _____ Organic Binders _____ Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Gravimetric (NOB) Required ☐ Recommended ☐ Gravimetric PREP ☐ Gravimetric (NOB) PLM ☐ Gravimetric (NOB) TEM ☐		Comments:		Q.C. ☐		
POINT COUNT RESULTS ON THE BACK		Method: ☐ ELAP + EPA ¹ ☐ ELAP ☐ EPA ¹ ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA ¹ First 4 preps. Asbestos = 0				
02	Color <u>Brown</u> Texture <u>Gr.</u>	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>100</u> Fiberglass _____ Other _____	Mineral Filler _____ Organic Binders _____ Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Gravimetric (NOB) Required ☐ Recommended ☐ Gravimetric PREP ☐ Gravimetric (NOB) PLM ☐ Gravimetric (NOB) TEM ☐		Comments:		Q.C. ☐		
POINT COUNT RESULTS ON THE BACK		Method: ☐ ELAP + EPA ¹ ☐ ELAP ☐ EPA ¹ ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA ¹ First 4 preps. Asbestos = 0				
03	Color <u>Brown</u> Texture <u>Gr.</u>	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>100</u> Fiberglass _____ Other _____	Mineral Filler _____ Organic Binders _____ Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Gravimetric (NOB) Required ☐ Recommended ☐ Gravimetric PREP ☐ Gravimetric (NOB) PLM ☐ Gravimetric (NOB) TEM ☐		Comments:		Q.C. ☐		
POINT COUNT RESULTS ON THE BACK		Method: ☐ ELAP + EPA ¹ ☐ ELAP ☐ EPA ¹ ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA ¹ First 4 preps. Asbestos = 0				
04	Color <u>Brown</u> Texture <u>Gr.</u>	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>15</u> Fiberglass _____ Other _____	Mineral Filler <u>85</u> Organic Binders _____ Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Gravimetric (NOB) Required ☐ Recommended ☐ Gravimetric PREP ☐ Gravimetric (NOB) PLM ☐ Gravimetric (NOB) TEM ☐		Comments:		Q.C. ☐		
POINT COUNT RESULTS ON THE BACK		Method: ☐ ELAP + EPA ¹ ☐ ELAP ☐ EPA ¹ ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA ¹ First 4 preps. Asbestos = 0				

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

CONFIDENTIAL,

CITY_21MC100_003473820

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

104 East 25th Street, 10th Floor - New York, NY 10010 - Phone (212) 353 - 8280, FAX (212) 353 - 3599 or 8306

NVLAP 101187

ELAP 10879

Microscope OLYMP BH 2

Client / Project NYC-BOE/PS 89M, 201 WARREN ST, NY, NY 10282 Project No. 14584-0819Analysis Date 04/26/02 Analyst E. A. CUNTEROS Batch No. 20315

Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
05	Color <u>Brown</u> Texture <u>Gr.</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes No	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Brief _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>20</u> Fiberglass _____ Other _____	Mineral Filler <u>80</u> Organic Binders _____ Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Comments: _____ Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0						
06	Color <u>Brown</u> Texture <u>Gr.</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes No	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Brief _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose _____ Fiberglass _____ Other _____	Mineral Filler <u>100</u> Organic Binders _____ Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Comments: _____ Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0						
07	Color <u>Brown</u> Texture <u>Gr.</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes No	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Brief _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose _____ Fiberglass _____ Other _____	Mineral Filler <u>100</u> Organic Binders _____ Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Comments: _____ Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0						
08	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes No	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Brief _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>20</u> Fiberglass _____ Other <u>15</u> <u>Hair</u>	Mineral Filler <u>50</u> Organic Binders <u>15</u> Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Comments: _____ Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0						

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

CONFIDENTIAL,

CITY_21MC100_003473821

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

104 East 25th Street, 10th Floor - New York, NY 10010 - Phone (212) 353 - 8280, FAX (212) 353 - 3599 or 8306

NVLAP 101187

ELAP 10879

Microscope OL YP BII 2

Client / Project NYC-BOE/PS 89M, 201 WARREN ST, NY, NY 10282 Project No. 14584-0819Analysis Date 04/26/02 Analyst E. A. GUARIGOS Batch No. 20315

Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
09	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes No	Morphology _____ RI I _____ DS Color _____ Brief _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>60</u> Fiberglass _____ Other <u>Synthetic & Hesi</u>	Mineral Filler <u>10</u> Organic Binders _____ Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0						Q.C. ☐
10	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes No	Morphology _____ RI I _____ DS Color _____ Brief _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>10</u> Fiberglass _____ Other _____	Mineral Filler <u>70</u> Organic Binders <u>20</u> Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0						Q.C. ☒ ND PA
11	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes No	Morphology _____ RI I _____ DS Color _____ Brief _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>15</u> Fiberglass _____ Other _____	Mineral Filler <u>70</u> Organic Binders <u>15</u> Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0						Q.C. ☐
12	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes No	Morphology _____ RI I _____ DS Color _____ Brief _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>10</u> Fiberglass _____ Other <u>Hesi</u>	Mineral Filler <u>65</u> Organic Binders <u>15</u> Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0						Q.C. ☐

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

CONFIDENTIAL,

CITY_21MC100_003473822

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

104 East 25th Street, 10th Floor - New York, NY 10010 - Phone (212) 353 - 8280, FAX (212) 353 - 3599 or 8306

NYLAP 101187

ELAP 10879

Microscope OLTP BH 2

Client / Project NYC-BOE/PS 89M, 201 WARREN ST, NY, NY 10282Project No. 14584-0819Analysis Date 04/26/02 Analyst E. A. CuatrecasasBatch No. 20315

Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
1 <u>13</u>	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Brief _____ Sign _____	☒ Chrysotile ☒ Amosite ☐ Other	<u>35</u> Cellulose Fiberglass Other	<u>65</u> Mineral Filler Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
Comments:			O.C. ☐			
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒			SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0			
2 <u>14</u>	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Brief _____ Sign _____	☒ Chrysotile ☒ Amosite ☐ Other	<u>30</u> Cellulose Fiberglass Other	<u>50</u> Mineral Filler <u>20</u> Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
Comments:			O.C. ☐			
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒			SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0			
3 <u>15</u>	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Brief _____ Sign _____	☒ Chrysotile ☒ Amosite ☐ Other	<u>35</u> Cellulose Fiberglass Other	<u>60</u> Mineral Filler <u>5</u> Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
Comments:			O.C. ☐			
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒			SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0			
4 <u>16</u>	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Brief _____ Sign _____	☒ Chrysotile ☒ Amosite ☐ Other	<u>20</u> Cellulose Fiberglass Other	<u>80</u> Mineral Filler Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
Comments:			O.C. ☐			
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒			SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0			

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

CONFIDENTIAL,

CITY_21MC100_003473823

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

101 East 25th Street, 10th Floor - New York, NY 10010 - Phone (212) 353 - 8280, FAX (212) 353 - 3599 or 8306

NVLAP 101187

ELAP 10879

Microscope OLYP BH 2

Client / Project NYC-BOE/PS 89M, 201 WARREN ST, NY, NY 10282Project No. 14584-0819Analysis Date 04/26/02 Analyst E. A. GUNTERSBatch No. 20315

Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
17	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes No Comments:	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	<u>/</u> Chrysotile Anosite Other	<u>60</u> Cellulose <u>30</u> Fiberglass <u>Synthetic</u> Other	<u>10</u> Mineral Filler Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0			Q.C. ☐			
18	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes No Comments:	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	<u>/</u> Chrysotile Anosite Other	<u>55</u> Cellulose <u>40</u> Fiberglass <u>Feather & Synthetic</u> Other	<u>5</u> Mineral Filler Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0			Q.C. ☐			
19	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes No Comments:	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	<u>/</u> Chrysotile Anosite Other	<u>20</u> Cellulose Fiberglass Other	<u>70</u> Mineral Filler <u>10</u> Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0			Q.C. ☐			
20	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes No Comments:	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	<u>/</u> Chrysotile Anosite Other	<u>10</u> Cellulose Fiberglass Other	<u>90</u> Mineral Filler Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0			Q.C. ☒ <u>NO PLM</u>			

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

CONFIDENTIAL,

CITY_21MC100_003473824

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

104 East 25th Street, 10th Floor - New York, NY 10010 - Phone (212) 353 - 8280, FAX (212) 353 - 3599 or 8306

NYLAP 101187

ELAP 10879

Microscope OLYP BH2

Client / Project NYC-BOE/PS 89M, 201 WARREN ST, NY, NY 10282Project No. 14584-0819Analysis Date 04/26/02 Analyst E. A. CUNNEANSBatch No. 20315

Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
21	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes ☐ No ☒	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>10</u> Fiberglass _____ Other <u>Hair</u>	Mineral Filler <u>70</u> Organic Binders <u>10</u> Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Comments:			Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps Asbestos = 0		POINT COUNT RESULTS ON THE BACK	
22	Color <u>White</u> Texture <u>Gr</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes ☐ No ☒	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose _____ Fiberglass _____ Other <u>Hair</u>	Mineral Filler <u>90</u> Organic Binders _____ Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Comments:			Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps Asbestos = 0		POINT COUNT RESULTS ON THE BACK	
23	Color <u>Brown</u> Texture <u>Gr</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes ☐ No ☒	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>10</u> Fiberglass _____ Other <u>Hair</u>	Mineral Filler <u>80</u> Organic Binders _____ Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Comments:			Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps Asbestos = 0		POINT COUNT RESULTS ON THE BACK	
24	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Color of Layer _____ Detected Yes ☐ No ☒	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>55</u> Fiberglass _____ Other <u>35</u> <u>Synthetic Hair</u>	Mineral Filler <u>10</u> Organic Binders _____ Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
Comments:			Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps Asbestos = 0		POINT COUNT RESULTS ON THE BACK	

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

CONFIDENTIAL,

CITY_21MC100_003473825

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

104 East 25th Street, 10th Floor - New York, NY 10010 - Phone (212) 353 - 8280, FAX (212) 353 - 3599 or 8306

NVLAP 101187

ELAP 10879

Microscope OL YP BH 2

Client / Project NYC-BOE/PS 89M, 201 WARREN ST, NY, NY 10282 Project No. 14584-0819Analysis Date 04/26/02 Analyst E. A. CUNTEROS Batch No. 20315

Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
25	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments: _____	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Brief _____ Sign _____	☒ Chrysotile ☐ Amosite ☐ Other	<u>50</u> Cellulose _____ Fiberglass <u>20</u> Other <u>Synthetic & Hair</u>	<u>30</u> Mineral Filler _____ Organic Binders _____ Vermiculite _____ Other	_____ Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0		POINT COUNT RESULTS ON THE BACK		Q.C. ☐		
26	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments: _____	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Brief _____ Sign _____	☒ Chrysotile ☐ Amosite ☐ Other	<u>60</u> Cellulose _____ Fiberglass <u>30</u> Other <u>Synthetic & Hair</u>	<u>10</u> Mineral Filler _____ Organic Binders _____ Vermiculite _____ Other	_____ Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0		POINT COUNT RESULTS ON THE BACK		Q.C. ☐		
27	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments: _____	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Brief _____ Sign _____	☒ Chrysotile ☐ Amosite ☐ Other	<u>20</u> Cellulose _____ Fiberglass <u>10</u> Other <u>Hair</u>	<u>70</u> Mineral Filler _____ Organic Binders _____ Vermiculite _____ Other	_____ Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0		POINT COUNT RESULTS ON THE BACK		Q.C. ☐		
28	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments: _____	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Brief _____ Sign _____	☒ Chrysotile ☐ Amosite ☐ Other	<u>65</u> Cellulose _____ Fiberglass <u>30</u> Other <u>Hair</u>	<u>5</u> Mineral Filler _____ Organic Binders _____ Vermiculite _____ Other	_____ Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos
Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0		POINT COUNT RESULTS ON THE BACK		Q.C. ☐		

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

CONFIDENTIAL,

CITY_21MC100_003473826

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

104 East 25th Street, 10th Floor - New York, NY 10010 - Phone (212) 353 - 8280, FAX (212) 353 - 3599 or 8306

NVLAP 101187

ELAP 10879

Microscope OL YP BH 2

Client / Project NYC-BOE/PS 89M, 201 WARREN ST, NY, NY 10282 Project No. 14584-0819Analysis Date 04/26/02 Analyst E. A. CUNTEROS Batch No. 20315

Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
29	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments:	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	10 Cellulose Fiberglass 60 Other <u>Feather & Hair</u>	80 Mineral Filler Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
POINT COUNT RESULTS ON THE BACK			Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0		d.c. ☐	
30	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments:	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	10 Cellulose Fiberglass Other	80 Mineral Filler 10 Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
POINT COUNT RESULTS ON THE BACK			Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0		d.c. ☐	
31	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments:	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	60 Cellulose Fiberglass 40 Other <u>Synthetic Hair</u>	10 Mineral Filler Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
POINT COUNT RESULTS ON THE BACK			Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0		d.c. ☐	
32	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments:	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	10 Cellulose Fiberglass Other	90 Mineral Filler Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
POINT COUNT RESULTS ON THE BACK			Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0		d.c. ☐	

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

CONFIDENTIAL,

CITY_21MC100_003473827

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

104 East 25th Street, 10th Floor - New York, NY 10010 - Phone (212) 353 - 8280, FAX (212) 353 - 3599 or 8306

NYLAP 101187

ELAP 10079

Microscope OLYMP BH2

Client / Project NYC-BOE/PS 89M, 201 WARREN ST, NY, NY 100282 Project No. 14584-0819Analysis Date 04/26/02 Analyst E. A. CHARTERS Batch No. 20315

Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
37	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments: _____ Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps Asbestos = 0	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	☒ Chrysotile ☒ Amosite ☒ Other	<u>10</u> Cellulose _____ Fiberglass _____ Other	<u>80</u> Mineral Filler <u>10</u> Organic Binders _____ Vermiculite _____ Other	_____ Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos
38	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments: _____ Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps Asbestos = 0	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	☒ Chrysotile ☒ Amosite ☒ Other	<u>5</u> Cellulose _____ Fiberglass _____ Other	<u>95</u> Mineral Filler _____ Organic Binders _____ Vermiculite _____ Other	_____ Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos
39	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments: _____ Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps Asbestos = 0	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	☒ Chrysotile ☒ Amosite ☒ Other	<u>70</u> Cellulose _____ Fiberglass <u>20</u> Other <u>Synthetic i Hair</u>	<u>10</u> Mineral Filler _____ Organic Binders _____ Vermiculite _____ Other	_____ Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos
40	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments: _____ Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps Asbestos = 0	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	☒ Chrysotile ☒ Amosite ☒ Other	<u>70</u> Cellulose _____ Fiberglass <u>20</u> Other <u>Synthetic i Hair</u>	<u>10</u> Mineral Filler _____ Organic Binders _____ Vermiculite _____ Other	_____ Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

CONFIDENTIAL,

CITY_21MC100_003473828

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

104 East 25th Street, 10th Floor - New York, NY 10010 - Phone (212) 353 - 8280, FAX (212) 353 - 3599 or 8306

NYLAP 101187

ELAP 10879

Microscope OLYMP BH-2

Client / Project NYC-BOE/PS 89M, 201 WARREN ST, NY, NY 10282Project No. 14584-0819Analysis Date 04/26/02 Analyst E. A. CARTERSBatch No. 20315

Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (HOB) Results %
1 33	Color <u>Brown/Grain</u> Texture <u>F/Fib</u> Homogeneity <u>N</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments: _____	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>30</u> Fiberglass _____ Other <u>Synthetic</u>	Mineral Filler <u>40</u> Organic Binders _____ Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
POINT COUNT RESULTS ON THE BACK Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0						
2 34	Color <u>Brown/Grain</u> Texture <u>F</u> Homogeneity <u>N</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments: _____	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>15</u> Fiberglass _____ Other _____	Mineral Filler <u>75</u> Organic Binders <u>10</u> Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
POINT COUNT RESULTS ON THE BACK Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0						
3 35	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments: _____	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>10</u> Fiberglass _____ Other <u>Synthetic & Hair</u>	Mineral Filler <u>40</u> Organic Binders <u>20</u> Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
POINT COUNT RESULTS ON THE BACK Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0						
4 36	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers _____ Asbestos ☐ ☒ Color of Layer _____ Detected Yes No Comments: _____	Morphology _____ Extinction _____ RI I _____ RI II _____ DS Color _____ Color, Pleo _____ Biref _____ Sign _____	Chrysotile _____ Amosite _____ Other _____	Cellulose <u>10</u> Fiberglass _____ Other _____	Mineral Filler <u>80</u> Organic Binders <u>10</u> Vermiculite _____ Other _____	Organic _____ Residue _____ Carbonate _____ Other _____ Asbestos _____
POINT COUNT RESULTS ON THE BACK Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0						

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

CONFIDENTIAL,

CITY_21MC100_003473829