NYC 9/11 Public Portal Document

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

101 East 25th Street, 10th Floor , New York, NY 10010 - Phone (212) 353 - 8200, FAX (212) 353 - 3599 or 0306

NVLAP Lab Code

ELAP Lab ID

Microscope ID: PLM #

Client / Project: NYC DOE / P.S. 92 Corona - HVAC Upgr Project No: 145[illegible]

Analysis Date: [illegible] Analyst: E. A Cabrera Batch No: 200[illegible]

Field ID: 25	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
Sub-sample (SAP) Prepared Recommended Confirm by PLM/TEM Confirm by PLM/TEM Point count (400)	Color: Brown Texture: F Homogeneity: Y # of Layers: Asbestos: ☐ ☑ Color of Layer: Detected: Yes No Comments:	Morphology: Extinction: RI I: RI ⊥: DS Color: Color,Pleo: Biref: Sign:	Chrysotile Amosite Other	10 Cellulose Fiberglass 10 Other Hair	25 Mineral Filler 5 Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
Point count (400)	Method: ☐ PLM + DS ☐ PLM ☐ DS ☐ other ☒ SCANNING OPTICAL PLM (EC 1.0 EPA) First 4 preps Asbestos = 0			Q.C. ☐		

Field ID: 26	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
Sub-sample (SAP) Prepared Recommended Confirm by PLM/TEM Confirm by PLM/TEM Point count (400)	Color: Brown Texture: F Homogeneity: Y # of Layers: Asbestos: ☐ ☑ Color of Layer: Detected: Yes No Comments:	Morphology: Extinction: RI I: RI ⊥: DS Color: Color,Pleo: Biref: Sign:	Chrysotile Amosite Other	20 Cellulose Fiberglass 10 Other Hair	65 Mineral Filler 5 Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
Point count (400)	Method: ☐ PLM + DS ☐ PLM ☐ DS ☐ other ☒ SCANNING OPTICAL PLM (EC 1.0 EPA) First 4 preps Asbestos = 0			Q.C. ☐		

Field ID: 27	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
Sub-sample (SAP) Prepared Recommended Confirm by PLM/TEM Confirm by PLM/TEM Point count (400)	Color: Brown Texture: F Homogeneity: Y # of Layers: Asbestos: ☐ ☑ Color of Layer: Detected: Yes No Comments:	Morphology: Extinction: RI I: RI ⊥: DS Color: Color,Pleo: Biref: Sign:	Chrysotile Amosite Other	15 Cellulose Fiberglass 5 Other Hair	75 Mineral Filler 5 Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
Point count (400)	Method: ☐ PLM + DS ☐ PLM ☐ DS ☐ other ☒ SCANNING OPTICAL PLM (EC 1.0 EPA) First 4 preps Asbestos = 0			Q.C. ☐		

Field ID: 28	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
Sub-sample (SAP) Prepared Recommended Confirm by PLM/TEM Confirm by PLM/TEM Point count (400)	Color: Brown Texture: F Homogeneity: V # of Layers: Asbestos: ☐ ☑ Color of Layer: Detected: Yes No Comments:	Morphology: Extinction: RI I: RI ⊥: DS Color: Color,Pleo: Biref: Sign:	Chrysotile Amosite Other	20 Cellulose Fiberglass 5 Other Hair	70 Mineral Filler 5 Organic Binders Vermiculite Other	Organic Residue Carbonate Other Asbestos
Point count (400)	Method: ☐ PLM + DS ☐ PLM ☐ DS ☐ other ☒ SCANNING OPTICAL PLM (EC 1.0 EPA) First 4 preps Asbestos = 0			Q.C. ☐		

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008 CONFIDENTIAL, CITY_21MC100_013183717

NYC-WTC_000178808