

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

104 East 25th Street, 10th Floor, New York, NY 10010 Phone (212) 353-8280, FAX (212) 353-3599 or 8306

INCLAP 101187

ELAP 10079

Microscope OLYMPUS

Client / Project NYC - BOE / P.S. 89 M, 201 WARREN ST, NY, NY 10282 Project No 14584-0819Analysis Date 03/15/02 Analyst E. A. CARREROS Batch No 20142

Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (HOB) Results %
37	Color <u>Brown</u> Texture <u>Fib</u> Homogeneity <u>Y</u> # of Layers <u>1</u> Asbestos ☐ ☒ Color of Layer <u> </u> Detected Yes No Comments:	Morphology <u> </u> Extinction <u> </u> RI I <u> </u> RI II <u> </u> DS Color <u> </u> Color, Pleo <u> </u> Biref <u> </u> Sign <u> </u>	☒ Chrysotile ☒ Amosite ☒ Other	<u>55</u> Cellulose <u>35</u> Fiberglass <u>35</u> Other Synthetic fibers	<u>10</u> Mineral Filler <u> </u> Organic Binders <u> </u> Vermiculite <u> </u> Other	<u> </u> Organic <u> </u> Residue <u> </u> Carbonate <u> </u> Other <u> </u> Asbestos
POINT COUNT RESULTS ON THE BACK	Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 prep. Asbestos = 0					
38	Color <u>Brown</u> Texture <u>Fib</u> Homogeneity <u>Y</u> # of Layers <u>1</u> Asbestos ☐ ☒ Color of Layer <u> </u> Detected Yes No Comments:	Morphology <u> </u> Extinction <u> </u> RI I <u> </u> RI II <u> </u> DS Color <u> </u> Color, Pleo <u> </u> Biref <u> </u> Sign <u> </u>	☒ Chrysotile ☒ Amosite ☒ Other	<u>65</u> Cellulose <u>30</u> Fiberglass <u>30</u> Other Synthetic fibers	<u>5</u> Mineral Filler <u> </u> Organic Binders <u> </u> Vermiculite <u> </u> Other	<u> </u> Organic <u> </u> Residue <u> </u> Carbonate <u> </u> Other <u> </u> Asbestos
POINT COUNT RESULTS ON THE BACK	Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 prep. Asbestos = 0					
39	Color <u>Brown</u> Texture <u>Fib</u> Homogeneity <u>Y</u> # of Layers <u>1</u> Asbestos ☐ ☒ Color of Layer <u> </u> Detected Yes No Comments:	Morphology <u> </u> Extinction <u> </u> RI I <u> </u> RI II <u> </u> DS Color <u> </u> Color, Pleo <u> </u> Biref <u> </u> Sign <u> </u>	☒ Chrysotile ☒ Amosite ☒ Other	<u>65</u> Cellulose <u>30</u> Fiberglass <u>30</u> Other Synthetic fibers	<u>5</u> Mineral Filler <u> </u> Organic Binders <u> </u> Vermiculite <u> </u> Other	<u> </u> Organic <u> </u> Residue <u> </u> Carbonate <u> </u> Other <u> </u> Asbestos
POINT COUNT RESULTS ON THE BACK	Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 prep. Asbestos = 0					
40	Color <u>Brown</u> Texture <u>F</u> Homogeneity <u>Y</u> # of Layers <u>1</u> Asbestos ☐ ☒ Color of Layer <u> </u> Detected Yes No Comments:	Morphology <u> </u> Extinction <u> </u> RI I <u> </u> RI II <u> </u> DS Color <u> </u> Color, Pleo <u> </u> Biref <u> </u> Sign <u> </u>	☒ Chrysotile ☒ Amosite ☒ Other	<u>55</u> Cellulose <u>15</u> Fiberglass <u>15</u> Other Synthetic fibers	<u>15</u> Mineral Filler <u> </u> Organic Binders <u> </u> Vermiculite <u> </u> Other	<u> </u> Organic <u> </u> Residue <u> </u> Carbonate <u> </u> Other <u> </u> Asbestos
POINT COUNT RESULTS ON THE BACK	Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 prep. Asbestos = 0		☒ ND MC			

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

CONFIDENTIAL,

CITY_21MC100_003390886