

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

104 East 25th Street, 10th Floor New York, NY 10010 Phone (212) 353-8280, FAX (212) 353-3599 or 8306

NVLAP 101187

ELAP 10879

Microscope OLYMP BH-2

Client / Project NYC-BOE/Stuyvesant
Analysis Date 4/17/2 Analyst CReepeProject No. 19125-0246
Batch No. 20273

1	Field No. <u>05</u>	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
	Gravimetric (NOB) Required ☐	Color <u>Grey</u> Texture <u>FR</u>	Morphology ☐ Extinction ☐	☐ Chrysotile <u>94</u>	Cellulose <u>6</u>	Mineral Filler <u>6</u>	Organic ☐
	Recommended ☐	Homogeneity <u>Y</u>	RI I ☐ RI II ☐	☐ Amosite	Fiberglass ☐	Organic Binders ☐	Residue ☐
	Gravimetric PREP ☐	# of Layers <u>1</u> Asbestos ☐ ☒	DS Color ☐ Color, Pleo ☐	☐ Other	Other ☐	Vermiculite ☐	Carbonate ☐
	Gravimetric (NOB) PLM ☐	Color of Layer ☐ Detected Yes No	Biref ☐ Sign ☐			Other ☐	Other ☐
	Gravimetric (NOB) TEM ☐	Comments:			Q.C. ☐		Asbestos ☐
POINT COUNT RESULTS ON THE BACK		Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0					

2	Field No. <u>06</u>	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
	Gravimetric (NOB) Required ☐	Color <u>Grey</u> Texture <u>FR</u>	Morphology ☐ Extinction ☐	☐ Chrysotile <u>94</u>	Cellulose <u>6</u>	Mineral Filler <u>6</u>	Organic ☐
	Recommended ☐	Homogeneity <u>Y</u>	RI I ☐ RI II ☐	☐ Amosite	Fiberglass ☐	Organic Binders ☐	Residue ☐
	Gravimetric PREP ☐	# of Layers <u>1</u> Asbestos ☐ ☒	DS Color ☐ Color, Pleo ☐	☐ Other	Other ☐	Vermiculite ☐	Carbonate ☐
	Gravimetric (NOB) PLM ☐	Color of Layer ☐ Detected Yes No	Biref ☐ Sign ☐			Other ☐	Other ☐
	Gravimetric (NOB) TEM ☐	Comments:			Q.C. ☐		Asbestos ☐
POINT COUNT RESULTS ON THE BACK		Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0					

3	Field No. <u>07</u>	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
	Gravimetric (NOB) Required ☐	Color <u>Grey</u> Texture <u>FR</u>	Morphology ☐ Extinction ☐	☐ Chrysotile <u>95</u>	Cellulose <u>5</u>	Mineral Filler <u>5</u>	Organic ☐
	Recommended ☐	Homogeneity <u>Y</u>	RI I ☐ RI II ☐	☐ Amosite	Fiberglass ☐	Organic Binders ☐	Residue ☐
	Gravimetric PREP ☐	# of Layers <u>1</u> Asbestos ☐ ☒	DS Color ☐ Color, Pleo ☐	☐ Other	Other ☐	Vermiculite ☐	Carbonate ☐
	Gravimetric (NOB) PLM ☐	Color of Layer ☐ Detected Yes No	Biref ☐ Sign ☐			Other ☐	Other ☐
	Gravimetric (NOB) TEM ☐	Comments:			Q.C. ☐		Asbestos ☐
POINT COUNT RESULTS ON THE BACK		Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0					

4	Field No. <u>08</u>	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
	Gravimetric (NOB) Required ☐	Color <u>Grey</u> Texture <u>FR</u>	Morphology ☐ Extinction ☐	☐ Chrysotile <u>95</u>	Cellulose <u>5</u>	Mineral Filler <u>5</u>	Organic ☐
	Recommended ☐	Homogeneity <u>Y</u>	RI I ☐ RI II ☐	☐ Amosite	Fiberglass ☐	Organic Binders ☐	Residue ☐
	Gravimetric PREP ☐	# of Layers <u>1</u> Asbestos ☐ ☒	DS Color ☐ Color, Pleo ☐	☐ Other	Other ☐	Vermiculite ☐	Carbonate ☐
	Gravimetric (NOB) PLM ☐	Color of Layer ☐ Detected Yes No	Biref ☐ Sign ☐			Other ☐	Other ☐
	Gravimetric (NOB) TEM ☐	Comments:			Q.C. ☐		Asbestos ☐
POINT COUNT RESULTS ON THE BACK		Method: ☐ ELAP + EPA ☐ ELAP ☐ EPA ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA First 4 preps. Asbestos = 0					

CONFIDENTIAL, SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

CITY_21MC100_001903118