

ATC Environmental, Inc.  
104 East 25th Street  
New York, New York 10010

N.Y.C. Board of Education  
28-11 Queens Plaza North  
Long Island City, NY 11101

Approved N.Y. State ELAP #10879  
ACCREDITED NVLAP Lab Code # 1187  
Report Date: 10/18/01

# ASBESTOS FIBER ANALYSIS BY TRANSMISSION ELECTRON MICROSCOPY (TEM)

With Fiber Identification by Selected-Area Electron Diffraction (SAED) and Energy-Dispersive X-RAY Spectroscopy (EDS)  
Method: AHERA Final Rule, EPA Federal Register (40 CFR, Part 763), Vol. 52, No. 210, October 30, 1987

## Sample Identification

## Analysis Parameters

Project/Site: New Stuyvesant H.S., 345 Chambers St., NY, NY

TEM Sample No.: 5716 - 61541

Exterior & Interior of Building & Roof

Grid Openings Analyzed: 4

Date Received: 10/17/01

Average Grid Opening: 106.00 um

Project Sample No.: NSHS-EIR-10/17-9

Total Area Analyzed: 0.0450 mm2

Air Volume: 1899 liters

Analytical Sensitivity: 22.2 s/mm2

Filter Type: MCE 25 mm diam., Pore Size: 0.45 um

Effective Area: 385 mm2

0.0045 s/cc

## FIBROUS PARTICULATES ANALYZED

### Number Observed

### CONCENTRATION

|                                                | Single |         |          | Matrix  |         | Total<br>Struct.<br>>=5um | Filter     |           | Air |
|------------------------------------------------|--------|---------|----------|---------|---------|---------------------------|------------|-----------|-----|
|                                                | Fibers | Bundles | Clusters | Struct. | Struct. |                           | Struct/mm2 | Struct/cc |     |
| Chrysotile Asbestos                            | 0      | 0       | 0        | 0       | 0       | 0                         | 0.0        | 0.0000    | 0   |
| Amphibole Asbestos                             | 0      | 0       | 0        | 0       | 0       | 0                         | 0.0        | 0.0000    | 0   |
| Ambiguous                                      | 0      | 0       | 0        | 0       | 0       | 0                         | 0.0        | 0.0000    | 0   |
| Total asbestos (includes ambiguous structures) |        |         |          |         | 0       | 0                         | 0.0        | 0.0000    | 0   |
| Non-Asbestos                                   | 0      | 0       | 0        | 0       | 0       | 0                         | 0.0        | 0.0000    | N/A |
| No Identification                              | 0      | 0       | 0        | 0       | 0       | 0                         | 0.0        | 0.0000    | N/A |
| Totals (All Structures)                        |        |         |          |         | 0       | 0                         | 0.0        | 0.0000    | N/A |

The estimated uncertainty of this analysis is 1 standard deviation.

Non-asbestos fiber i.d. (EDS/SAED): None detected

Amphibole Asbestos Type: None detected

The Analysis was carried out in accordance with the approved TEM method.  
This laboratory is in compliance with the quality specified for the method.

Analyzed by:

Report Reviewed by:

Marek Peysakhov

Michael A. Gorycki, Ph.D.  
Director of Electron Microscopy