NYC 9/11 Public Portal Document

ASBESTOS ANALYTICAL REPORT

DEP

DIVISION OF EMERGENCY RESPONSE AND TECHNICAL ASSESSMENT
ASBESTOS LABORATORY
96-05 HORACE HARDING EXPRESSWAY
CORONA, NEW YORK 11368
(718) 595-6309 FAX# (718) 595-6307

ELAP # 11045

TEST METHODS : 1) 40 CFR Part 763, Subpart F, App. A
2) Polarized Light Microscopy plus Stratified Point-Counting Method
3) EPA/600/R-93/116

Incident #: TRU0273MN03
Inspector : R. RAMMOHAN
Premise : 114 LIBERTY STREET
Boro : Manhattan
Analyst : G. ROMAN

Date Collected: 03/27/03
Received: 03/27/03
Analyzed: 03/27/03

Client #:		
DEP Sample #:	30327/A078004	30327/A078005
Laboratory #:	30327/376	30327/377
Location Sampled:	PIZZARIA ON TABLE	ON DROP CEILING
Color:	BEIGE	BEIGE
Homogenous:	Yes	No
Asbestos Present:	Yes	Yes

Results (%)

Amosite	44.5	Chrysotile	3.1
Cellulose	trace	Quartz	65.4
Fibrous glass	33.3	Matrix	31.5
Matrix	22.2		

Comments: 1.Sample #005 has 2 types of material
2.This report has results for the beige cementitious material.

Reviewed by: A. Adelman
Laboratory Director

This test report may not be reproduced except with the written approval of this laboratory. The test report relates only to the item(s) listed and does not represent a product endorsement by NVLAP or any other U.S. Government agency.

NYC-WTC_000186829