

ATTACHMENT 3

Lower Manhattan Testing

Collection Date: 9/11/01

WTC PLM Sample Analysis Table

Location Sampled	Sample Type	Asbestos Fiber Types	Fiber 2	Fiber 3
23 Barclay St	Bulk	CHRY 1%	—	—
217 Broadway	Bulk	CHRY 4%	Cell 76%	Fiberglass 17%
Church St. & Vesey St	Bulk	—	Cell 45%	Fiberglass 30%
Church St. & Vesey St	Bulk	CHRY 1.3%	—	—
Across 90 Church St	Bulk	—	Cell 2%	Fiberglass 98%
Barclay St & Church St	Bulk	CHRY 4.8%	—	—
Warren St & Church St	Bulk	CHRY Trace	—	—
Church St & Murray St	Bulk	CHRY <1%	—	—
Park Pl & Church St	Bulk	CHRY 4% Almost Trace	—	—
Church St. & Dey St	Bulk	CHRY <1%	—	—
Church St & Cortlandt St	Bulk	CHRY <1%:Almost <1%	Cell 4%	Fiberglass 50%

BULK + WIPE
SAMPLING
Asbestos