

02/26/2002 13:00 6314676905
02/26/2002 11:41 5169977528

PEDNEAULT ASSOCIATES
EMSL

PAGE 14
PAGE 14

EMSL Analytical, Inc.

208 Stonching Lane
Carle Place, NY 11514
Phone: (516) 997-7251 Fax: (516) 997-7528

EMSL

Attn.:

Pedneault Associates, Inc.
1615 Ninth Avenue
Bohemia, NY 11716

Tuesday, February 26, 2002

Ref Number: LI023221

POLARIZED LIGHT MICROSCOPY (PLM) - POINT COUNT

Performed by EPA 600/R-93/116 Method*

Project: 20 W.S. Man

Sample	Location	Appearance	Sample Treatment	ASBESTOS		NON-ASBESTOS	
				%	Type	% Fibrous	% Non-Fibrous
230		Grey Fibrous Heterogeneous	Tossed	None Detected		20.% Cellulose 20.% Min. Wool	80.% Other
231		Grey Fibrous Heterogeneous	Tossed	0.24% Chrysotile		20.% Cellulose 20.% Min. Wool	59.76% Other
232		Grey Fibrous Heterogeneous	Tossed	None Detected		10.% Cellulose 10.% Min. Wool	80.% Other
233		Grey Fibrous Heterogeneous	Tossed	Trace Chrysotile		20.% Cellulose 20.% Min. Wool	80.% Other
234		Grey Fibrous Heterogeneous	Tossed	None Detected		10.% Cellulose 10.% Min. Wool	80.% Other
235		Grey Fibrous Heterogeneous	Tossed	None Detected		10.% Cellulose 10.% Min. Wool	80.% Other

Comments: For all obviously heterogeneous samples easily separated into subsamples, and for layered samples, each component is analyzed separately. Also, "# of Layers" refers to number of separable subsamples.

* NY samples analyzed by ELAP 198.1 Method.

Daniel Clarke
Analyst

Approved
Signatory

Disclaimer: PLM has been known to miss asbestos in a small percentage of samples which contain asbestos. Thus negative PLM results cannot be guaranteed. EMSL suggests that samples reported as <1% or none detected be tested with either SEM or TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL. The above test must not be used by the client to claim product endorsement by NVLAP nor any agency of the United States Government. Laboratory is not responsible for the accuracy of results when requested to physically separate and analyze layered samples.

Analysis performed by EMSL Long Island (NY) ELAP and Bulk #101000-10, NY ELAP 11469, CA ELAP 2339, CT ELAP 0241

FEB-26-2002 12:26

6314676905

96%

P.14

CITY_21MC100_002953697

02/26/2002 13:00 6314676905
 02/26/2002 11:41 5169977528

PEDNEAULT ASSOCIATES
 EMSL

PAGE 15
 PAGE 15

EMSL Analytical, Inc.

208 Stonehinge Lane
 Carle Place, NY 11514

Phone: (516) 997-7251 Fax: (516) 997-7528

EMSL

Attn.:

Pedneault Associates, Inc.
 1615 Ninth Avenue
 Bohemia, NY 11716

Tuesday, February 26, 2002

Ref Number: LI023221

POLARIZED LIGHT MICROSCOPY (PLM) - POINT COUNT

Performed by EPA 600/R-93/116 Method*

Project: 20 W.S. Man

Sample	Location	Appearance	Sample Treatment	ASBESTOS		NON-ASBESTOS	
				%	Type	%	Fibrous % Non-Fibrous
236		Gray Fibrous Heterogeneous	Teased	Trace	Chrysotile	10.0% Cellulose 10.0% Min. Wool	80.0% Other
237		Gray Fibrous Heterogeneous	Teased	0.23%	Chrysotile	10.0% Cellulose 10.0% Min. Wool	79.77% Other
238		Gray Fibrous Heterogeneous	Teased	None Detected		10.0% Cellulose 10.0% Min. Wool	80.0% Other
236 QC		Gray Fibrous Heterogeneous	Teased	None Detected		10.0% Cellulose 10.0% Min. Wool	80.0% Other

Comments: For all obviously heterogeneous samples easily separated into subsamples, and for layered samples, each component is analyzed separately. Also, "N of Layers" refers to number of separable subsamples.

* NY samples analyzed by ELAP 198.1 Method.

Daniel Clarke
 Analyst

Approved
 Signatory

Disclaimers: PLM has been known to miss asbestos in a small percentage of samples which contain asbestos. Thus negative PLM results cannot be guaranteed. EMSL suggests that samples reported as 41% or none detected be tested with either SEM or TEM. This above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL. The above test must not be used by the client to claim product endorsement by NVLAP nor any agency of the United States Government. Laboratory is not responsible for the accuracy of results when requested to physically separate and analyze layered samples.

2

Analysis performed by EMSL, 208 Stonehinge Lane, Carle Place, NY 11514-1000, NY PLAP 11468, CA ELAP 2239, CT PH0249

FEB-26-2002 12:27

6314676905

98%

P.15

CITY_21MC100_002953698