

ATC Environmental, Inc.
104 East 25th Street
New York, New York 10010

N.Y.C. Board of Education
28-11 Queens Plaza North
Long Island City, NY 11101

Approved N.Y. State ELAP #10879
ACCREDITED NVLAP Lab Code # 1187
Report Date: 10/27/01

ASBESTOS FIBER ANALYSIS BY TRANSMISSION ELECTRON MICROSCOPY (TEM)

With Fiber Identification by Selected-Area Electron Diffraction (SAED) and Energy-Dispersive X-RAY Spectroscopy (EDS)
Method: AHERA Final Rule, EPA Federal Register (40 CFR, Part 763), Vol. 52, No. 210, October 30, 1987

Sample Identification

Analysis Parameters

Project/Site: New Stuyvesant H.S., 345 Chambers St., NY, NY

Exterior & Interior of Building & Roof

TEM Sample No.: 5775 - 62366

Date Received: 10/26/01

Grid Openings Analyzed: 4

Project Sample No.: 5

Average Grid Opening: 106.00 um

Air Volume: 1928 liters

Total Area Analyzed: 0.0450 mm2

Filter Type: MCE 25 mm diam., Pore Size: 0.45 um

Analytical Sensitivity: 22.2 s/mm2

Effective Area: 385 mm2

0.0044 s/cc

FIBROUS PARTICULATES ANALYZED

Number Observed

CONCENTRATION

	Single			Matrix	Total.	Total Struct. =>Sum	Filter		Air
	Fibers	Bundles	Clusters	Struct.	Struct.		Struct/mm2	Struct/cc	
Chrysotile Asbestos	0	0	0	0	0	0	0.0	0.0000	0
Amphibole Asbestos	0	0	0	0	0	0	0.0	0.0000	0
Ambiguous	0	0	0	0	0	0	0.0	0.0000	0
Total asbestos (includes ambiguous structures)					0	0	0.0	0.0000	0
Non-Asbestos	0	0	0	0	0	0	0.0	0.0000	N/A
No Identification	0	0	0	0	0	0	0.0	0.0000	N/A
Totals (All Structures)					0	0	0.0	0.0000	N/A

The estimated uncertainty of this analysis is 1 standard deviation.

Non-asbestos fiber i.d. (EDS/SAED): None detected

Amphibole Asbestos Type: None detected

The Analysis was carried out in accordance with the approved TEM method.
This laboratory is in compliance with the quality specified for the method.

Analyzed by:

Report Reviewed by:

Marek Peysakhov

Michael A. Gorycki, Ph.D.
Director of Electron Microscopy