

09/13/2001 16:30 2125450757

ADVANCED ENVIRONMENT

PAGE 01

09/13/2001 16:17 212-290-0058

EMSL MANHATTAN

PAGE 01

New York Lab

307 West 38th Street, New York, NY 10018

Phone: 212-290-0051 Fax: 212-290-0058 Email:

EMSL

Attn: Mr Robert Puorro / Mr Edward Namath
Advanced Environmental Corp.
347 Fifth Avenue
Suite 404
New York, NY 10018

Fax: (212) 545-0757 Phone: 212-545-1855

Project: 1015-038 Silverstein 140 Broadway

Customer ID: ADVA57
Customer PO:
Received: 09/13/01 2:29 PM

EMSL Order: 030104195
EMSL Project ID:
Analysis Date: 9/13/2001

Asbestos Analysis of Bulk Materials by PLM via the NY State ELAP 198.1 Method

Sample	Location	Appearance	Treatment	Non-Asbestos		Asbestos	
				% Fibrous	% Non-Fibrous	% Type	
031301RP01 030104195-0001	Debris-Lobby adjacent security desk	Gray Fibrous Heterogeneous	Teased	25.00% Min. Wool 20.00% Cellulose	43.62% Non-fibrous (other) 10.00% CA Carbonite	1.38% Chrysotile <1% Amosite	
031301RP02 030104195-0002	Debris-Lobby adj elevator bank 21- 27	Tan Fibrous Heterogeneous	Teased	35.00% Min. Wool 10.00% Cellulose	25.00% Non-fibrous (other) 20.00% Matrix 10.00% CA Carbonite	<1% Chrysotile	
031301RP03 030104195-0003	Debris-Lobby Cedar St side adj revolving dr	Tan/Gray Fibrous Heterogeneous	Teased	35.00% Min. Wool 15.00% Cellulose	25.00% Non-fibrous (other) 15.00% Matrix 10.00% CA Carbonite	<1% Chrysotile	
031301RP04 030104195-0004	Debris-Lobby adjacent elevator bank 1-10	Gray Fibrous Heterogeneous	Teased	35.00% Min. Wool 10.00% Cellulose	25.00% Non-fibrous (other) 15.00% Matrix 15.00% CA Carbonite	<1% Chrysotile	
031301RP05 030104195-0005	Debris-Lobby corner Nassau/Cedar St	Gray Fibrous Heterogeneous	Teased	30.00% Min. Wool 15.00% Cellulose	25.00% Non-fibrous (other) 20.00% Matrix 10.00% CA Carbonite	<1% Chrysotile	
031301RP06 030104195-0006	Debris-Lobby Cedar St side adjacent doors	Gray/Tan Fibrous Heterogeneous	Teased	25.00% Min. Wool 10.00% Cellulose	30.00% Non-fibrous (other) 20.00% Matrix 15.00% CA Carbonite	<1% Chrysotile	
031301RP07 030104195-0007	Debris-Lobby within convenience store	Gray Fibrous Heterogeneous	Teased	30.00% Min. Wool 10.00% Cellulose	25.00% Non-fibrous (other) 25.00% Matrix 10.00% CA Carbonite	<1% Chrysotile	

Gulam Machhiwala

Analyst



Laboratory Manager
or other approved signatory

PLM has been known to miss asbestos in a small percentage of samples which contain asbestos. Negative PLM results cannot be guaranteed. Samples reported as <1% or none detected should be tested with TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL. Analysis, Inc. The above test must not be used by the client to claim product endorsement by NYLAP nor any agency of the United States Government.

Analysis performed by EMSL Manhattan (NYLAP #101048-9), NY ELAP 11506

PLM Print Count: 1

1

SEP 13 2001 16:52

2125450757

PAGE 01

CITY_DEP_WORBY_CANNATA_SUBP_000007121

09/13/2001 16:17

212-290-0058

EMSL MANHATTAN

PAGE 02

New York Lab

307 West 38th Street, New York, NY 10018

Phone: 212-290-0051 Fax: 212-290-0058 Email:

EMSL

Attn: Mr Robert Puorro / Mr Edward Namath
Advanced Environmental Corp.
347 Fifth Avenue
Suite 404
New York, NY 10018

Customer ID: ADVA57
Customer PO:
Received: 09/13/01 2:29 PM

Fax: (212) 545-0757 Phone: 212-545-1855
Project: 1015-038 Silverstein 140 Broadway

EMSL Order: 030104195
EMSL Project ID:
Analysis Date: 9/13/2001

Asbestos Analysis of Bulk Materials by PLM via the NY State ELAP 198.1 Method

Sample	Location	Appearance	Treatment	Non-Asbestos		Asbestos	
				% Fibrous	% Non-Fibrous	% Type	
031301RP08 030104195-0008	Debris-Lobby former bank space	Gray Fibrous Heterogeneous	Teased	35.00% Min. Wool 15.00% Cellulose	23.56% Non-fibrous (other) 15.00% Matrix 10.00% CA Carbonite	1.44% Chrysotile	
031301RP09 030104195-0009	Debris-Lobby former bank space	Gray Fibrous Heterogeneous	Teased	25.00% Min. Wool 10.00% Cellulose	25.00% Non-fibrous (other) 30.00% Matrix 10.00% CA Carbonite	<1% Chrysotile	
031301RP10 030104195-0010	Debris-Fir 14 fresh air intake	Gray Fibrous Heterogeneous	Teased	25.00% Min. Wool 15.00% Cellulose	35.00% Non-fibrous (other) 15.00% Matrix 10.00% CA Carbonite	<1% Chrysotile	
031301RP11 030104195-0011	Debris- Level 3B fresh air intake	Gray Fibrous Heterogeneous	Teased	25.00% Min. Wool 10.00% Cellulose	33.80% Non-fibrous (other) 20.00% Matrix 10.00% CA Carbonite	1.20% Chrysotile	

Gulam Machhiwala

Analyst



Laboratory Manager
or other approved signatory

PLM has been known to miss asbestos in a small percentage of samples which contain asbestos. Negative PLM results cannot be guaranteed. Samples reported as <1% or none detected should be tested with TEM. This above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical, Inc. The above test must not be used by the client to claim product endorsement by NVLAP nor any agency of the United States Government. Analysis performed by EMSL Manhattan (NVLAP #101048-9), NY ELAP 11506

PLM Print Count-1

2