NYC 9/11 Public Portal Document

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1920 |
| **Lab Group #:** | 9210 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 8 | **Grid Opening Size:** | 0 01124 |
| **Client Sample #:** | 10 | **Area Examined:** | 0 04496 mm² |
| **GRID BOX:** | 1 | **Magnification:** | 20,000 |
| **GRID ID:** | ZRS | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 12/26/200 |

**Analysis Performed By:** MP
MARK PEYSAKHOV

| GO No | GO Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 | R1 | NSD | | | | | | | | | | | |
| 2 | V1 | — | | | | | | | | | | | |
| 3 | J8 | — | | | | | | | | | | | |
| 4 | R5 | — | | | | | | | | | | | |

^ Photo No (from 1 in 5 asbestos containing samples)
Struct = > 0 5µ > 5 1 Aspect Ratio
√= Positive diffraction pattern properties conforming to laboratory identification criteria observed
√= EDS spectrum conforming to laboratory identification criteria observed
F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance
<50% undissolved filter, overlapped or folded
<10% particulate coverage >50% coverage ate least 20 unfolded or overlaoped grid squares
<5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

## Totals

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |



NYC-WTC_000196857