NYC 9/11 Public Portal Document

ATC ASSOCIATES INC - NEW YORK BULK ASBESTOS ANALYSIS SHEET

104 East 25th Street, 10th Floor · New York, NY 10010 · Phone (212) 353 - 8280, FAX (212) 353 - 3599 or 8306

NVLAP 101187
ELAP 10870
Microscope OLYP BH-2

Client / Project NYC-BOE/P.S. 89M, 201 Warren St. NY.NY. Project No. 14584-0819

Analysis Date 12/11/01 Analyst E. A. Cuan Tenos Batch No. 19836

1 Field No. 5	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
Gravimetric (NOB) Required ☐	Color Brown Texture F	Morphology Wavy Extinction P	Trace Chrysotile	33 Cellulose	47 Mineral Filler	___ Organic
Recommended ☒	Homogenity Y	RI l 1.549 RI ll 1.550	___ Amosite	20 Fiberglass	___ Organic Binders	___ Residue
Gravimetric PREP ☐	# of Layers ___ Asbestos ☒ ☐	DS Color B/M Color,Pleo N	___ Other	___ Other	___ Vermiculite	___ Carbonate
Gravimetric (NOB) PLM ☐	Color of Layer ___ Detected Yes No	Biref L Sign P			___ Other	___ Other
Gravimetric (NOB) TEM ☐	Comments:			Q.C. ☐		___ Asbestos
POINT COUNT RESULTS ON THE BACK	Method: ☒ ELAP + EPA¹ ☐ ELAP ☐ EPA¹ ☐ OTHER ☐ SCANNING OPTION: ELAP (P.C.) & EPA¹ First 4 preps. Asbestos = 0					

2 Field No. 6	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
Gravimetric (NOB) Required ☐	Color Brown Texture F	Morphology ___ Extinction ___	___ Chrysotile	30 Cellulose	48 Mineral Filler	___ Organic
Recommended ☐	Homogenity Y	RI l ___ RI ll ___	___ Amosite	22 Fiberglass	___ Organic Binders	___ Residue
Gravimetric PREP ☐	# of Layers ___ Asbestos ☐ ☒	DS Color ___ Color,Pleo ___	___ Other	___ Other	___ Vermiculite	___ Carbonate
Gravimetric (NOB) PLM ☐	Color of Layer ___ Detected Yes No	Biref ___ Sign ___			___ Other	___ Other
Gravimetric (NOB) TEM ☐	Comments:			Q.C. ☐		___ Asbestos
POINT COUNT RESULTS ON THE BACK	Method: ☐ ELAP + EPA¹ ☐ ELAP ☐ EPA¹ ☐ OTHER ☒ SCANNING OPTION: ELAP (P.C.) & EPA¹ First 4 preps. Asbestos = 0					

3 Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
Gravimetric (NOB) Required ☐	Color ___ Texture ___	Morphology ___ Extinction ___	___ Chrysotile	___ Cellulose	___ Mineral Filler	___ Organic
Recommended ☐	Homogenity ___	RI l ___ RI ll ___	___ Amosite	___ Fiberglass	___ Organic Binders	___ Residue
Gravimetric PREP ☐	# of Layers ___ Asbestos ☐ ☐	DS Color ___ Color,Pleo ___	___ Other	___ Other	___ Vermiculite	___ Carbonate
Gravimetric (NOB) PLM ☐	Color of Layer ___ Detected Yes No	Biref ___ Sign ___			___ Other	___ Other
Gravimetric (NOB) TEM ☐	Comments:			Q.C. ☐		___ Asbestos
POINT COUNT RESULTS ON THE BACK	Method: ☐ ELAP + EPA¹ ☐ ELAP ☐ EPA¹ ☐ OTHER ☐ SCANNING OPTION: ELAP (P.C.) & EPA¹ First 4 preps. Asbestos = 0					

4 Field No.	Stereoscopic Exam	PLM Optical Properties	Asbestos Results PLM %	Other Fibrous %	Non Fibrous %	Gravimetric (NOB) Results %
Gravimetric (NOB) Required ☐	Color ___ Texture ___	Morphology ___ Extinction ___	___ Chrysotile	___ Cellulose	___ Mineral Filler	___ Organic
Recommended ☐	Homogenity ___	RI l ___ RI ll ___	___ Amosite	___ Fiberglass	___ Organic Binders	___ Residue
Gravimetric PREP ☐	# of Layers ___ Asbestos ☐ ☐	DS Color ___ Color,Pleo ___	___ Other	___ Other	___ Vermiculite	___ Carbonate
Gravimetric (NOB) PLM ☐	Color of Layer ___ Detected Yes No	Biref ___ Sign ___			___ Other	___ Other
Gravimetric (NOB) TEM ☐	Comments:			Q.C. ☐		___ Asbestos
POINT COUNT RESULTS ON THE BACK	Method: ☐ ELAP + EPA¹ ☐ ELAP ☐ EPA¹ ☐ OTHER ☐ SCANNING OPTION: ELAP (P.C.) & EPA¹ First 4 preps. Asbestos = 0					

CITY_21MC100_000330786

NYC-WTC_000198910