

**New York Lab**

307 West 38th Street, New York, NY 10018

Phone: 212-290-0051 Fax: 212-290-0058 Email:

**EMSL**

Attn: U.S. EPA - Residential  
 HQ Financial Services Division  
 1200 Pennsylvania Ave. NW Maildrop 2734R  
 Washington, DC 20460

Fax: Phone:  
 Project: USPS MISSION #12: RESIDENTIAL SAMPLING NEW  
 YORK CITY / BLDG 28/110 GREENWICH

Customer ID: USEPA44  
 Customer PO: 2W-1103-NNLX  
 Received: 12/03/01 7:27 PM

EMSL Order: 030109058  
 EMSL Project ID:  
 Analysis Date: 12/4/01

**Asbestos Analysis of Bulk Materials by PLM via the NY State ELAP 198.1 Method**

| Sample                        | Location    | Appearance                             | Treatment           | Non-Asbestos                                               |                                                   | Asbestos      |
|-------------------------------|-------------|----------------------------------------|---------------------|------------------------------------------------------------|---------------------------------------------------|---------------|
|                               |             |                                        |                     | % Fibrous                                                  | % Non-Fibrous                                     | % Type        |
| (R)SA-O-28<br>030109058-0001  | OUTDOORS    | Tan<br>Fibrous<br>Heterogeneous        | Teased<br>Dissolved | 15.00% Glass<br>20.00% Cellulose                           | 30.00% Non-fibrous (other)<br>35.00% CA Carbonite | None Detected |
| (R)VA-C-28<br>030109058-0002  | COMMON AREA | Brown<br>Fibrous<br>Heterogeneous      | Teased<br>Dissolved | 10.00% Glass<br>20.00% Fibrous (other)<br>25.00% Cellulose | 45.00% Non-fibrous (other)                        | None Detected |
| (R)VA-R1-28<br>030109058-0003 | RESIDENCE 1 | Brown/Gray<br>Fibrous<br>Heterogeneous | Teased<br>Dissolved | 20.00% Hair<br>40.00% Fibrous (other)<br>30.00% Cellulose  | 10.00% Non-fibrous (other)                        | None Detected |
| (R)VA-R2-28<br>030109058-0004 | RESIDENCE 2 | Tan/Blue<br>Fibrous<br>Heterogeneous   | Teased<br>Dissolved | 60.00% Fibrous (other)<br>20.00% Cellulose                 | 20.00% Non-fibrous (other)                        | None Detected |

Williams John

Analyst

*E. B. B.*

Laboratory Manager  
 or other approved signatory

PLM has been known to miss asbestos in a small percentage of samples which contain asbestos. Negative PLM results cannot be guaranteed. Samples reported as <1% or none detected should be tested with TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical, Inc. The above text must not be used by the client to claim product endorsement by NYLAP nor any agency of the United States Government.

PLM Pointcount-1

1