

New York Lab

307 West 38th Street, New York, NY 10018

Phone: 212-290-0051 Fax: 212-290-0058 Email:

EMSL

Attn: U. S. EPA
 HQ Financial Services Division
 1200 Pennsylvania Ave. NW Maildrop 2734R
 Washington, DC 20460

Customer ID: USEPA30
 Customer PO: 2W-1104-NNLX
 Received: 11/17/01 6:17 PM

Fax: Phone:
 Project: BLDG. 7 / 55 LIBERTY ST. / SIE

EMSL Order: 030108206
 EMSL Project ID:
 Analysis Date: 11/18/2001

Polarized Light Microscopy (PLM) Performed by NIOSH Method 9002, Issue 2

Sample	Location	Appearance	Treatment	Non-Asbestos		Asbestos
				% Fibrous	% Non-Fibrous	% Type
[R]SA-O-7 030108206-0001	OUTDOORS NEXT TO FRT. ENTRANCE	Gray Fibrous Heterogeneous	Teased	35% Glass 5% Fibrous (other) 10% Cellulose	25% Quartz 25% Non-fibrous (other)	None Detected
[R]VA-C-7 030108206-0002	21ST FLOOR HALLWAY	Gray Fibrous Heterogeneous	Teased	5% Glass 10% Fibrous (other) 55% Cellulose	30% Non-fibrous (other)	None Detected
[R]VA-R1-7 030108206-0003	FLOOR 21 APT. 21C	Gray Fibrous Heterogeneous	Teased	5% Hair 10% Fibrous (other) 65% Cellulose	20% Non-fibrous (other)	None Detected
[R]VA-R2-7 030108206-0004	FLOOR 21 APT. 21B	Gray Fibrous Heterogeneous	Teased	5% Glass 15% Fibrous (other) 55% Cellulose	25% Non-fibrous (other)	None Detected
[R]SA-R2-7 030108206-0005	OUTSIDE ON WINDOW	Gray Fibrous Heterogeneous	Teased	40% Glass 5% Fibrous (other) 5% Cellulose	20% Quartz 30% Non-fibrous (other)	None Detected

Analyst(s)

Alex Chechelovski (5)

Eir B. B.
 Laboratory Manager
 or other approved signatory

Disclaimer: PLM has been known to miss asbestos in a small percentage of samples which contain asbestos. Thus negative PLM results cannot be guaranteed. EMSL suggests that samples reported as <1% or none detected be tested with either SEM or TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL. The above test must not be used by the client to claim product endorsement by NVLAP nor any agency of the United States Government. Laboratory is not responsible for the accuracy of results when requested to physically separate and analyze layered samples.

