# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1928 |
| **Lab Group #:** | 7902 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 7 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 7 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | 1179 | **Magnification:** | 20,000 |
| **GRID ID:** | HHJ | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 5/30/02 |

**Analysis Performed By:** RP

ROMAN PEYSAKHOV

| GO. No | GO. Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | Length >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 | J2 | N00 | | | | | | | | | | | |
| 2 | Q2 | 1 | | | | | | | | | | | |
| 3 | P2 | 1 | | | | | | | | | | | |
| 4 | I2 | 1 | | | | | | | | | | | |
| 45 | | | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber

B = Bundle (<3 fibers <1 fiber diameter apart

C = Cluster (>3 Intersections)

M = Matrix

NSD = No Structures Detected

Grid acceptance:

<50% undissolved filter, overlapped or folded

<10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES

Amosite

Crocidolite

Anthophyllite

Tremolite

Actinolite

## Totals

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |