

JLC ENVIRONMENTAL CONSULTANTS, INC.
 200 Park Avenue South, Suite 1001, New York, New York 10003
 Phone: (212) 420-8119 Fax: (212) 420-6092

Metcalf & Eddy Inc.
 3 Werner Way, Suite 310
 Lebanon, NJ 08833

ELAP Lab Code: 11029
 NIOSH and AIHA Lab Code: 100273
 NVLAP Lab Code: 101953

Project No.: 01-2102
 Analyte: ASBESTOS
 Date Received: 9/28/01
 Date Analyzed: 9/29/01
 Batch #: 0109B385

SUMMARY OF ANALYTICAL RESULTS - PLM

Site: 3 World Financial Center - Floors 3-26

SAMPLE

DATE
COLLECTED

DESCRIPTION / LOCATION

COLOR

ASBESTOS
DETECTED?

TOTAL % OF
ASBESTOS

CONSTITUENTS

LAB #

CLIENT'S SAMPLE #

12001 9/28/01 10967	12th Floor/ South East/ East/ Nelson Soures' Office/ Sample of Debris	GRAY	NO	0%	CELL NFIB	20% 80%
12-001						
12002 9/28/01 10968	12th Floor/ South East/ South/ Mike McCully's Office/ Sample of Debris	BROWN	NO	0%	CELL NFIB	35% 65%
12-002						
12003 9/28/01 10969	12th Floor/ South East/ East/ Mike McCully's Office/ Sample of Debris	BROWN	NO	0%	CELL NFIB	30% 70%
12-003						
12004 9/28/01 10970	12th Floor/ South East/ East/ Mike McCully's Office/ Sample of Debris	GRAY/ WHITE	YES	12.5%	CHRY CELL NFIB	12.5% 25.0% 62.5%
12-004						

*INSUFFICIENT MATERIAL SUBMITTED

**TEM RECOMMENDED

***NOT ANALYZED POSITIVE STOP

Sample Analysis by:

Polarized Light Microscopy-Dispersion Staining (PLM-DS)

Method of Sample Preparation and Analysis:

All samples were prepared and analyzed in accordance with the EPA Method for the Determination of Asbestos in Bulk Building Materials USEPA/ 600/ R-93/116, July 1993.

Instrumentation:


Olympus PLM, Model BH-2/VM Stereomicroscope, Model VMZ 1x-4x.

ASBESTOS CONSTITUENTS

CHRY = Chrysotile Asbestos
 AMOS = Amosite Asbestos
 CROC = Crocidolite Asbestos
 ACTN = Actinolite Asbestos
 TREM = Tremolite Asbestos
 ANTH = Anthophyllite Asbestos

NON-ASBESTOS CONSTITUENTS

PAPF = Paper Fiber
 MINW = Mineral Wool
 FBGL = Fiberglass
 SYNFF = Synthetic Fibers
 CELL = Cellulose
 NFIB = Non-Fibrous
 ORGM = Organic Material
 WOLL = Wollastonite
 HSHR = Horse Hair
 OTHR = Other


Gulam Machhiwala
 Laboratory Director

Analytical results reflect the make up of the materials only in the areas sampled. This "Summary of Analytical Results" shall not be reproduced except in full, without the written approval of JLC Laboratory, and it must not be used by client to claim product endorsement by NVLAP or any agency of the U.S. Government. This method is not applicable to samples containing large amounts of fine fibers below the resolution of the light microscope. The value of this method is limited to the quantitative identification of asbestos and the semi-quantitative determination of asbestos content of bulk samples, expressed as a percentage of the protected area. Quantitation of asbestos content was determined with a visual volume estimate, a calibrated visual area estimate, and/or point counting procedure. CAUTION: Other fibers with optical properties similar to asbestos may give positive interferences and will be considered asbestos under this methodology. Also, PLM is not consistently reliable in detecting asbestos in floor coverings and similar non-friable organically-bound materials. Quantitative transmission electron microscopy is currently the only method that can be used to determine if this material is considered or treated as non-asbestos containing.

JLC ENVIRONMENTAL CONSULTANTS, INC.
 200 Park Avenue South, Suite 1001, New York, New York 10003
 Phone: (212) 420-8119 Fax: (212) 420-6092

Metcalf & Eddy Inc.
 3 Werner Way, Suite 310
 Lebanon, NJ 08833

ELAP Lab Code: 11029
 NIOSH and AIHA Lab Code: 100273
 NVLAP Lab Code: 101953

Project No.: 01-2102
 Analyte: ASBESTOS
 Date Received: 9/28/01
 Date Analyzed: 9/29/01
 Batch #: 0109B385

SUMMARY OF ANALYTICAL RESULTS - PLM

Site: 3 World Financial Center - Floors 3-26

SAMPLE #	DESCRIPTION / LOCATION	COLOR	ASBESTOS DETECTED?	TOTAL % OF ASBESTOS	CONSTITUENTS	
DATE COLLECTED						
LAB #						
CLIENT'S SAMPLE #						
12005 9/28/01 10971	12th Floor/ South East/ East/ Joe Kelly's Office/ Sample of Debris	BEIGE	NO	0%	NFIB	100%
12-005 12006 9/28/01 10972	12th Floor/ South East/ East/ Joe Kelly's Office/ Sample of Debris	WHITE	NO	0%	NFIB	100%
12-006 12007 9/28/01 10973	12th Floor/ South East/ East/ Joe Kelly's Office/ Sample of Debris	GRAY	NO	0%	NFIB	100%
12-007 12008 9/28/01 10974	12th Floor/ South East/ East Side-South/ Mike Carter/ Sample of Debris	GRAY	NO	0%	FBGL NFIB	20% 80%
12-008						

*INSUFFICIENT MATERIAL SUBMITTED

**TEM RECOMMENDED

***NOT ANALYZED POSITIVE STOP

Sample Analysis by:

Polarized Light Microscopy-Dispersion Staining (PLM-DS)

Method of Sample Preparation and Analysis:

All samples were prepared and analyzed in accordance with the EPA
 "Method for the Determination of Asbestos in Bulk Building Materials"
 USEPA/ 600/ R-93/116, July 1993.

Instrumentation:


Olympus PLM, Model BH-2/VM Stereomicroscope, Model
 VMZ 1x-4x.

ASBESTOS CONSTITUENTS

CHRY = Chrysotile Asbestos
 AMOS = Amosite Asbestos
 CROC = Crocidolite Asbestos
 ACTN = Actinolite Asbestos
 TREM = Tremolite Asbestos
 ANTH = Anthophyllite Asbestos

NON-ASBESTOS CONSTITUENTS

PAPF = Paper Fiber
 MINW = Mineral Wool
 FBGL = Fiberglass
 SYNFF = Synthetic Fibers
 CELL = Cellulose
 NFIB = Non-Fibrous
 ORGM = Organic Material
 WOLL = Wollastonite
 HSHR = Horse Hair
 OTHR = Other


Gulam Machhiwala
 Laboratory Director

Analytical results reflect the make up of the materials only in the areas sampled. This "Summary of Analytical Results" shall not be reproduced except in full, without the written approval of JLC Laboratory, and it must not be used by client to claim product endorsement by NVLAP or any agency of the U.S. Government. This method is not applicable to samples containing large amounts of fine fibers below the resolution of the light microscope. The value of this method is limited to the quantitative identification of asbestos and the semi-quantitative determination of asbestos content of bulk samples, expressed as a percentage of the protected area. Quantitation of asbestos content was determined with a visual volume estimate, a calibrated visual area estimate, and/or point counting procedure. CAUTION: Other fibers with optical properties similar to asbestos may give positive interferences and will be considered asbestos under this methodology. Also, PLM is not consistently reliable in detecting asbestos in floor coverings and similar non-friable organically-bound materials. Quantitative transmission electron microscopy is currently the only method that can be used to determine if this material can be considered or treated as non-asbestos containing.

JLC ENVIRONMENTAL CONSULTANTS, INC.
 200 Park Avenue South, Suite 1001, New York, New York 10003
 Phone: (212) 420-8119 Fax: (212) 420-6092

Metcalf & Eddy Inc.
 3 Werner Way, Suite 310
 Lebanon, NJ 08833

ELAP Lab Code: 11029
 NIOSH and AIHA Lab Code: 100273
 NVLAP Lab Code: 101953

Project No.: 01-2102
 Analyte: ASBESTOS
 Date Received: 9/28/01
 Date Analyzed: 9/29/01
 Batch #: 0109B385

SUMMARY OF ANALYTICAL RESULTS - PLM

Site: 3 World Financial Center - Floors 3-26

SAMPLE #

**DATE
COLLECTED**

DESCRIPTION / LOCATION

COLOR

**ASBESTOS
DETECTED?**

**TOTAL % OF
ASBESTOS**

CONSTITUENTS

LAB #

CLIENT'S SAMPLE #

12009	12th Floor/ South East/ East Side-South/	GRAY	NO	0%	FBGL	25%
9/28/01	Mike Carter/ Sample of Debris				NFIB	75%
10975						
12-009						

*INSUFFICIENT MATERIAL SUBMITTED

**TEM RECOMMENDED

***NOT ANALYZED POSITIVE STOP

Sample Analysis by:

Polarized Light Microscopy-Dispersion Staining (PLM-DS)

Method of Sample Preparation and Analysis:

All samples were prepared and analyzed in accordance with the EPA "Method for the Determination of Asbestos in Bulk Building Materials" USEPA/ 600/ R-93/116, July 1993.

Instrumentation:


Olympus PLM, Model BH-2/VM Stereomicroscope, Model VMZ 1x-4x.

ASBESTOS CONSTITUENTS

CHRY = Chrysotile Asbestos
 AMOS = Amosite Asbestos
 CROC = Crocidolite Asbestos
 ACTN = Actinolite Asbestos
 TREM = Tremolite Asbestos
 ANTH = Anthophyllite Asbestos

NON-ASBESTOS CONSTITUENTS

PAPF = Paper Fiber
 MINW = Mineral Wool
 FBGL = Fiberglass
 SYNf = Synthetic Fibers
 CELL = Cellulose
 NFIB = Non-Fibrous
 ORGM = Organic Material
 WOLL = Wollastonite
 HSHR = Horse Hair
 OTHR = Other


Gulam Machhiwala
 Laboratory Director

Analytical results reflect the make up of the materials only in the areas sampled. This "Summary of Analytical Results" shall not be reproduced except in full, without the written approval of JLC Laboratory, and it must not be used by client to claim product endorsement by NVLAP or any agency of the U.S. Government. This method is not applicable to samples containing large amounts of fine fibers below the resolution of the light microscope. The value of this method is limited to the quantitative identification of asbestos and the semi-quantitative determination of asbestos content of bulk samples, expressed as a percentage of the protected area. Quantitation of asbestos content was determined with a visual volume estimate, a calibrated visual area estimate, and/or point counting procedure. CAUTION: Other fibers with optical properties similar to asbestos may give positive interferences and will be considered asbestos under this methodology. Also, PLM is not consistently reliable in detecting asbestos in floor coverings and similar non-friable organically-bound materials. Quantitative transmission electron microscopy is currently the only method that can be used to determine if this material can be considered or treated as non-asbestos containing.