

ASBESTOS ANALYTICAL REPORT **DEP**

DIVISION OF EMERGENCY RESPONSE AND TECHNICAL ASSESSMENT
ASBESTOS LABORATORY
96-05 HORACE HARDING EXPRESSWAY
CORONA, NEW YORK 11368
(718) 595-6309 FAX# (718) 595-6307

ELAP # 11045

TEST METHODS : 1) 40 CFR Part 763, Subpart F, App. A
2) Polarized Light Microscopy plus Stratified Point-Counting Method
3) EPA/600/R-93/116

Incident #: TRU0273MN03
Inspector : R. RAMMOHAN
Premise : 114 LIBERTY STREET
Boro : Manhattan
Analyst : G. ROMAN

Date Collected: 03/27/03
Received: 03/27/03
Analyzed: 03/27/03

Client #:

DEP Sample #:	30327/A078004	30327/A078005
Laboratory #:	30327/376	30327/377
Location Sampled:	PIZZARIA ON TABLE	ON DROP CEILING
Color:	BEIGE	BEIGE
Homogenous:	Yes	No
Asbestos Present:	Yes	Yes

Results (t)

Amosite	44.5	Chrysotile	3.1
Cellulose	trace	Quartz	65.4
Fibrous glass	33.3	Matrix	31.5
Matrix	22.2		

Comments: 1. Sample #005 has 2 types of material
 2. This report has results for the beige cementitious material.

Reviewed by: *G. Roman*
 Laboratory Director

This test report may not be reproduced except with the written approval of this laboratory. The test report relates only to the item(s) listed and does not represent a product endorsement by NVLAP or any other U.S. Government agency.