

AMBIENT LABS, INC.
159 WEST 25TH STREET
NEW YORK, NY 10001

BULK SAMPLE LABORATORY DATA REPORT

PROJECT : O211512
CLIENT : AMEX Towers
LOCATION : 3 World Financial Center
TECHNICIAN :

COLLECTED : 11/6/2001
DATE REC'D : 11/7/2001
TIME REC'D : 11:42 AM
ANALYZED : 11/13/2001

BATCH ID : 3429

SIGNED FOR AMBIENT LABS INC. BY:

LABORATORY ID NUMBER	FIELD ID NUMBER	SAMPLE COLOR	SAMPLE DESCRIPTION	ASBESTOS PRESENT	PERCENT OF TOTAL ASBESTOS		SAMPLE CONSTITUENTS
B2K91779	16-13A	GREY	INCOLUM CASE.	NAD	0.00 %	(P)	CELLULOSE : 20.00 % MINERAL WOOL : 40.00 % NON-FIBROUS : 40.00 %
B2K91780	16-14A	GREY	INCOLUM CASE.	YES	0.30 %	(P)	CHRYSTOTILE : .30 % CELLULOSE : 30.00 % MINERAL WOOL : 30.00 % NON-FIBROUS : 39.70 %
B2K91781	16-15A	GREY	INCOLUM CASE.	NAD	0.00 %	(P)	CELLULOSE : 30.00 % MINERAL WOOL : 30.00 % NON-FIBROUS : 40.00 %
B2K91782	16-16A	GREY	WEST PHONE CLOSET FLOOR.	NAD	0.00 %	(P)	CELLULOSE : 20.00 % MINERAL WOOL : 40.00 % NON-FIBROUS : 40.00 %
B2K91783	16-17A	GREY	ELECTRICAL WEST FLOOR.	NAD	0.00 %	(P)	CELLULOSE : 10.00 % MINERAL WOOL : TRACE NON-FIBROUS : 90.00 %
B2K91784	16-18A	GREY	MEN ROOM.	NAD	0.00 %	(P)	CELLULOSE : 10.00 % MINERAL WOOL : 10.00 % NON-FIBROUS : 80.00 %
B2K91785	16-19A	GREY	INSIDE ROOM FLOOR.	NAD	0.00 %	(P)	CELLULOSE : 20.00 % MINERAL WOOL : 20.00 % NON-FIBROUS : 60.00 %

NAD = No Asbestos Detected. Trace < 0.25 %.

(P) Analysis by Polarized Light Microscopy (PLM) NYS ELAP method 198.1 or EPA/600/R-93/116. (T) Analysis by Transmission Electron Microscopy (TEM) NYS ELAP method 198.4. Polarized Light Microscopy is not consistently reliable in detection of asbestos in floor coverings and similar non-friable organically bound materials. Quantitative transmission electron microscopy is currently the only method that can be used to determine if this material can be considered or treated as non-asbestos containing. No reproduction of all or any portion of this report shall occur without written approval of Ambient Labs, Inc. All results disclosed in this report relate only to the items tested.

NVLAP ID # 101618. NYS ELAP ID # 10865. STATE OF CA ELAP ID # 2139.

CITY_21MC100_002840080

AMBIENT LABS, INC.
159 WEST 25TH STREET
NEW YORK, NY 10001

BULK SAMPLE LABORATORY DATA REPORT

PROJECT : 0211512
CLIENT : AMEX Towers
LOCATION : 3 World Financial Center
TECHNICIAN :

COLLECTED : 11/6/2001
DATE REC'D : 11/7/2001
TIME REC'D : 11:44 AM
ANALYZED : 11/13/2001

BATCH ID : 3429

SIGNED FOR AMBIENT LABS INC. BY:

LABORATORY ID NUMBER	FIELD ID NUMBER	SAMPLE COLOR	SAMPLE DESCRIPTION	ASBESTOS PRESENT	PERCENT OF TOTAL ASBESTOS	SAMPLE CONSTITUENTS
B2K91786	16-20A	GREY	ROOM ACROSS WTC.	YES	0.80 % (P)	CHRYSTILE : .80 % CELLULOSE : 30.00 % MINERAL WOOL : 30.00 % NON-FIBROUS : 39.20 %
B2K91787	16-21A	GREY	FRANK NAPOLITANO WINDOWSILL NORTHEAST.	YES	0.80 % (P)	CHRYSTILE : .80 % CELLULOSE : 30.00 % MINERAL WOOL : 30.00 % NON-FIBROUS : 39.20 %
B2K91788	16-13		INCOLUM CASE.	NAD	0.00 % ()	
B2K91789	16-14		INCOLUM CASE.	NAD	0.00 % ()	
B2K91790	16-15		INCOLUM CASE.	NAD	0.00 % ()	
B2K91791	16-16		WEST PHONE CLOSET FLOOR.	NAD	0.00 % ()	
B2K91792	16-17		ELECTRICAL WEST FLOOR.	NAD	0.00 % ()	
B2K91793	16-18		MEN ROOM.	NAD	0.00 % ()	
B2K91794	16-19		INSIDE ROOM FLOOR.	NAD	0.00 % ()	
B2K91795	16-19		ROOM ACROSE WTC.	NAD	0.00 % ()	

NAD = No Asbestos Detected. Trace < 0.25 %.

(P) Analysis by Polarized Light Microscopy (PLM) NYS ELAP method 198.1 or EPA/600/R-93/116. (T) Analysis by Transmission Electron Microscopy (TEM) NYS ELAP method 198.4. Polarized Light Microscopy is not consistently reliable in detection of asbestos in floor coverings and similar non-friable organically bound materials. Quantitative transmission electron microscopy is currently the only method that can be used to determine if this material can be considered or treated as non-asbestos containing. No reproduction of all or any portion of this report shall occur without written approval of Ambient Labs, Inc. All results disclosed in this report relate only to the items tested.

NVLAP ID # 101618. NYS ELAP ID # 10865. STATE OF CA ELAP ID # 2139.

CITY_21MC100_002840081