

EMSL Analytical, Inc.308 Stonehenge Lane
Carle Place, NY 11514

Phone: (516) 997-7251 Fax: (516) 997-7528

EMSL

Attn:

Ambient Lab, Inc.
159 West 25th Street
8th Floor
New York, NY 10018

Friday, November 16, 2001

Ref Number: LI0117346

POLARIZED LIGHT MICROSCOPY (PLM) - POINT COUNT


Performed by EPA 600/R-93/116 Method*

Project: AMEX TOWER 3 WORLD FINANCIAL CENTER NYC, NY

Sample	Location	Appearance	Sample Treatment	ASBESTOS		NON-ASBESTOS	
				%	Type	%	Fibrous % Non-Fibrous
22-04A	CONFERENCE RM	Grey Non-Fibrous Homogeneous	Teased	None Detected			100% Other
22-05A	ELEVATOR CENTER N	Grey Fibrous Homogeneous	Teased	None Detected		90% Cellulose	10% Other
22-06A	1 WIN SKILL S/E	Grey Fibrous Homogeneous	Teased/Crushed	None Detected		40% Cellulose 10% Min. Wool	50% Other
22-07A	2 WIN SKILL S/E	Black Non-Fibrous Heterogeneous	Crushed	None Detected		5% Cellulose	95% Other
22-08A	ELLIS WILKINS TOP DESK	Grey Fibrous Homogeneous	Teased	None Detected		30% Cellulose 40% Min. Wool	30% Other
22-09A	CONF RM	Grey Fibrous Homogeneous	Teased	None Detected		30% Cellulose 40% Min. Wool	30% Other


Comments: For all obviously heterogeneous samples easily separated into subsamples, and for layered samples, each component is analyzed separately. Also, "n of Layers" refers to number of separate subsamples.

* NY samples analyzed by ELAP 198.1 Method.


Daniel Clarke
Analyst

Approved
Signatory

Disclaimer: PLM has been shown to miss asbestos in a small percentage of samples which contain asbestos. This negative PLM results cannot be overridden. EMSL suggests that samples reported as "1% or none detected" be tested with either SEM or TEM. The above test report relates only to the tests listed. This report may not be reproduced, except in full, without written approval by EMSL. The above test must not be used by the client to claim asbestos abatement by NYLAP nor any agency of the United States Government. Laboratory is not responsible for the accuracy of results when requested to analyze separately and layered layered samples.

Analysis performed by EMSL Long Island (NYLAP AP and Buh #1010-10-10, NY ELAP 1145, CA ELAP 2235, CT PH-0248)



EMSL Analytical, Inc.
 208 Stonehenge Lane
 Carle Place, NY 11514
 Phone: (516) 997-7251 Fax: (516) 997-7528
EMSL

Attn:

 Ambient Lab, Inc.
 159 West 25th Street
 8th Floor
 New York, NY 10018

Friday, November 16, 2001

Ref Number: LI0117346

POLARIZED LIGHT MICROSCOPY (PLM) - POINT COUNT

Performed by EPA 600/R-93/116 Method*

Project: AMEX TOWER 3 WORLD FINANCIAL CENTER NYC, NY


Sample	Location	Appearance	Sample Treatment	ASBESTOS		NON-ASBESTOS	
				%	Type	% Fibrous	% Non-Fibrous
22-10A	CONF RM 324	Grey Fibrous Homogeneous	Teased	Trace	Chrysotile	30.% Cellulose 40.% Min. Wool	30.% Other
22-11A	9 WIN SILL E	Grey Fibrous Homogeneous	Teased	1.7%	Chrysotile	30.% Cellulose 40.% Min. Wool	28.3% Other
22-12A	MARY ANN OFF TOP EXHAUST	Grey Fibrous Homogeneous	Teased	None	Detected	30.% Cellulose 40.% Min. Wool	30.% Other
22-13A	CONF RM 300	Tan Non-Fibrous Homogeneous	Crushed	None	Detected	40.% Cellulose	50.% Other
22-14A	ROBERT VERITY TOP OF EXHAUST	Grey Fibrous Homogeneous	Teased	Trace	Chrysotile	20.% Cellulose 60.% Min. Wool	20.% Other
22-15A	CORR TOP CABINET	Grey Fibrous Homogeneous	Teased	None	Detected	60.% Cellulose 20.% Min. Wool	20.% Other

Comments: For all obviously heterogeneous samples easily separated into subsamples, and for layered samples, each component is analyzed separately. Also, "% of Layers" refers to number of separable subsamples.

* NY samples analyzed by ELAP 199.1 Method.



 Daniel Clarke
 Analyst



 Approved
 Signatory

Disclaimer: PLM has been known to miss asbestos in a small percentage of samples which contain asbestos. True negative PLM results cannot be guaranteed. EMSL suggests that samples reported as <1% or none detected be tested with other SEM or TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL. The above test must not be used by the client to claim product endorsement by NALAP nor any agency of the United States Government. Laboratory is not responsible for the accuracy of results when requested to analyze layered and/or analyzed layered samples.

Analysis performed by EMSL Long Island (NALAP) Air and Soil 9101045-10, NY ELAP 11469, CA ELAP 2338, CT PH-0246

AMBIENT GROUP, INC. - LONG ISLAND (516) 609-8271
11/16/2001 16:25 5169977528

11/17/01 03:01P P.020
EMSL LI

PAGE 1/12b-

EMSL Analytical, Inc.

208 Stonehenge Lane
Carle Place, NY 11514

Phone: (516) 997-7251 Fax: (516) 997-7528

EMSL

Attn:

Ambient Lab, Inc.
159 West 25th Street
8th Floor
New York, NY 10018

Friday, November 16, 2001

Ref Number: LJ0117346

POLARIZED LIGHT MICROSCOPY (PLM) - POINT COUNT


Performed by EPA 600/R-93/116 Method*

Project: AMEX TOWER 3 WORLD FINANCIAL CENTER NYC, NY

Sample	Location	Appearance	Sample Treatment	ASBESTOS		NON-ASBESTOS	
				%	Type	%	Fibrous Non-Fibrous
22-18A	WILLIAM BLOMQUIST TOP BKSHELF	Tan Fibrous Heterogeneous	Tossed/Crushed	None Detected		50.0% Cellulose	50.0% Other
22-17A	CONF RM R01	Black Fibrous Heterogeneous	Tossed	None Detected		5.0% Cellulose 10.0% Min. Wool	85.0% Other
22-18A	HALLWAY TOP TABLE	Gray Fibrous Homogeneous	Tossed	None Detected		10.0% Cellulose 80.0% Min. Wool	30.0% Other
22-19A	NY TRADING RM TOP DESK	Gray Fibrous Homogeneous	Tossed	0.46% Chrysotile		20.0% Cellulose 40.0% Min. Wool	39.84% Other
22-20A	NY TRADING RM CAB	Gray Fibrous Homogeneous	Tossed	None Detected		20.0% Cellulose 40.0% Min. Wool	40.0% Other
22-21A	MEN RM TOP VANITY	Gray Fibrous Homogeneous	Tossed	None Detected		30.0% Cellulose 40.0% Min. Wool	30.0% Other

Comments: For all obviously heterogeneous samples easily separated into subsamples, and for layered samples, each component is analyzed separately. Also, "N of Layers" refers to number of separable subsamples.

* NY samples analyzed by ELAP 194.1 Method.


Daniel Clarke
Analyst


Approved
Signatory

Disclaimer: PLM has been shown to miss asbestos in a small percentage of samples which contain asbestos. Thus negative PLM results cannot be guaranteed. EMSL suggests that samples reported as "100% or none detected" be tested with either TEM or TCM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL. The above test must not be used by the client to claim product endorsement by NYLAP nor any agency of the United States Government. Laboratory is not responsible for the accuracy of results when subjected to physically separate and analyze layered samples.

*Analysis performed by EMSL Long Island (NYLAP LI) and Bldg 8401048-10, NY ELAP 11408, CA ELAP 2330, CT PH-0248)