

AMBIENT LABS, INC.
159 WEST 25TH STREET
NEW YORK, NY 10001

BULK SAMPLE LABORATORY DATA REPORT

PROJECT : O211512
CLIENT : AMEX Towers
LOCATION : 3 World Financial Center
TECHNICIAN :

COLLECTED : 11/7/2001
DATE REC'D : 11/9/2001
TIME REC'D : 4:35 PM
ANALYZED : 11/7/2001

BATCH ID : 3442

SIGNED FOR AMBIENT LABS INC. BY:

LABORATORY ID NUMBER	FIELD ID NUMBER	SAMPLE COLOR	SAMPLE DESCRIPTION	ASBESTOS PRESENT	PERCENT OF TOTAL ASBESTOS		SAMPLE CONSTITUENTS
B2K91909	26-04	Gray	NORTHWEST CORNER TRAINING ROOM 2 / WINDOW SILL.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %
B2K91910	26-05	Gray	NORTHWEST TRAINING ROOM 2 / SHELF OPPOSITE WINDOW.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %
B2K91911	26-06	Gray	TRAINING ROOM 1 / MIDDLE TABLE ROW 5.	NAD	0.00 %	(P)	MINERAL WOOL : 5.00 % NON-FIBROUS : 95.00 %
B2K91912	26-07	Gray	TRAINING ROOM 1 / SHELF.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %
B2K91913	26-08	Gray	RECEPTION AREA / BABY GRAND PIANO.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %
B2K91914	26-09	Gray	ADJACENT AUDITORIUM ROOM DOOR.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %
B2K91915	26-10	Gray	RECEPTION AREA / CORNER TABLE.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %
B2K91916	26-11	Gray	ROOM 4 / BLACK TABLE.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %
B2K91917	26-12	Gray	ROOM 4 / BACK CLOSET SHELF.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %
B2K91918	26-13	Gray	ROOM 5 / FRONT TABLE TOP NORTH SIDE.	NAD	0.00 %	(P)	MINERAL WOOL : 15.00 % NON-FIBROUS : 85.00 %

NAD = No Asbestos Detected. Trace < 0.25 %.

(P) Analysis by Polarized Light Microscopy (PLM) NYS ELAP method 198.1 or EPA/600/R-93/116. (T) Analysis by Transmission Electron Microscopy (TEM) NYS ELAP method 198.4. Polarized Light Microscopy is not consistently reliable in detection of asbestos in floor coverings and similar non-friable organically bound materials. Quantitative transmission electron microscopy is currently the only method that can be used to determine if this material can be considered or treated as non-asbestos containing. No reproduction of all or any portion of this report shall occur without written approval of Ambient Labs, Inc. All results disclosed in this report relate only to the items tested.

NVLAP ID # 101618. NYS ELAP ID # 10865. STATE OF CA ELAP ID # 2139.

CITY_21MC100_002840107

AMBIENT LABS, INC.
159 WEST 25TH STREET
NEW YORK, NY 10001

BULK SAMPLE LABORATORY DATA REPORT

PROJECT : 0211512
CLIENT : AMEX Towers
LOCATION : 3 World Financial Center
TECHNICIAN :

COLLECTED : 11/7/2001
DATE REC'D : 11/9/2001
TIME REC'D : 4:37 PM
ANALYZED : 11/7/2001

BATCH ID : 3442

SIGNED FOR AMBIENT LABS INC. BY:

LABORATORY ID NUMBER	FIELD ID NUMBER	SAMPLE COLOR	SAMPLE DESCRIPTION	ASBESTOS PRESENT	PERCENT OF TOTAL ASBESTOS		SAMPLE CONSTITUENTS
B2K91919	26-14	Gray	TRAINING ROOM 6 / TABLE TOP FIRST ROW.	NAD	0.00 %	(P)	MINERAL WOOL : 15.00 % NON-FIBROUS : 85.00 %
B2K91920	26-15	Gray	PROJECTION ROOM.	NAD	0.00 %	(P)	MINERAL WOOL : 5.00 % NON-FIBROUS : 95.00 %
B2K91921	26-16	Gray	TRAINING ROOM 7 TABLE.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %
B2K91922	26-17	Gray	LOBBY FLOOR.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %
B2K91923	26-18	Gray	ROLE PLAY ROOM 12 / TABLE TOP.	NAD	0.00 %	(P)	MINERAL WOOL : 5.00 % NON-FIBROUS : 95.00 %
B2K91924	26-19	Gray	PROJECTION ROOM.	NAD	0.00 %	(P)	MINERAL WOOL : 5.00 % NON-FIBROUS : 95.00 %
B2K91925	26-20	Gray	SOUTH SIDE AREA ADJACENT ROLE PLUS ROOM TEN.	NAD	0.00 %	(P)	MINERAL WOOL : 5.00 % NON-FIBROUS : 95.00 %
B2K91926	26-21	Gray	ELEVATOR BANK FLOOR ELEVATOR THREE.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %
B2K91927	26-22	Gray	ON THE 28TH FLOOR LANDING STAIRS.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %
B2K91928	25-02	Gray	NORTHEAST MECHANICAL ROOM BENCH TOP.	NAD	0.00 %	(P)	MINERAL WOOL : 10.00 % NON-FIBROUS : 90.00 %

NAD = No Asbestos Detected. Trace < 0.25 %.

(P) Analysis by Polarized Light Microscopy (PLM) NYS ELAP method 198.1 or EPA/600/R-93/116. (T) Analysis by Transmission Electron Microscopy (TEM) NYS ELAP method 198.4. Polarized Light Microscopy is not consistently reliable in detection of asbestos in floor coverings and similar non-friable organically bound materials. Quantitative transmission electron microscopy is currently the only method that can be used to determine if this material can be considered or treated as non-asbestos containing. No reproduction of all or any portion of this report shall occur without written approval of Ambient Labs, Inc. All results disclosed in this report relate only to the items tested.

NVLAP ID # 101618. NYS ELAP ID # 10865. STATE OF CA ELAP ID # 2139.

CITY_21MC100_002840108