

ENVIRO-PROBE, INC.

2917 Bruckner Boulevard - Bronx, New York 10461

Phone: (718) 863-0045 - Fax: (718) 518-7454

BULK MATERIAL ANALYSIS FOR ASBESTOS

TEST METHOD - POLARIZED LIGHT MICROSCOPY - EPA/600/R-93/116, July 1993

NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM LAB ID# 101222

NEW YORK STATE ENVIRONMENTAL LABORATORY APPROVAL PROGRAM LAB ID# 10898

CLIENT NAME Central Env. Services
 COMPANY
 ADDRESS
 CITY, STATE, ZIP

DATE SUBMITTED: 9/24/01
 DATE ANALYZED: 9/24/01
 DATE REPORTED: 9/26/01
 LAB FILE # 23312
 ANALYST S. K. Dewan

1. SAMPLING LOCATION		67/69 Wall St., NY. Various Floors			
2. CLIENT'S ID#	37	38			
3. LAB ID#	B01-	20309	20310		
4. STEREO-MICROSCOPIC EXAMINATION					
1. HOMOGENEOUS (Y/N)	N	N			
2. COLOR	1 & 4	1 & 4			
1. WHITE					
2. BROWN					
3. GRAY					
4. OTHERS					
5. ASBESTOS DETECTED (YES/NO)	N	N			
6. ASBESTOS PERCENTAGE					
1. AMOSITE					
2. CHRYSOTILE					
3. CROCIDOLITE					
4. OTHERS					
7. TOTAL ASBESTOS PERCENTAGE	0	0			
8. PERCENTAGE - OTHER FIBROUS MATERIALS					
1. CELLULOSE					
2. FIBROUS GLASS	15	20			
3. OTHERS	30	25			
9. NON-FIBROUS MATERIALS					
1. CARBONATES	15	15			
2. SILICATES	10	15			
3. OTHERS	30	25			
10. TOTAL	100	100			

This report shall not be reproduced except in full, without the written approval of the laboratory

For quantitation purposes 1% is the concentration at which there is an uncertainty

These results apply to these/these particular samples/sample

o This report is not endorsed by NVLAP or any other U.S. Government Agency

... Traces = < 1%

LAB DIRECTOR/SUPERVISOR'S SIGNATURE

CITY_21MC100_002388393