

**Polarized Light Microscopy (PLM) Results, EPA/600/R-93/116 (NYS ELAP 198.1) Point Count Method**  
**RJ Lee Group Project No. LSH204785**

Analyst: WHP

**Analysis Report for Gash Emergency Samples collected 06/05/02**

| Sample ID                       | RJ Lee Group Sample ID | Building/Location (desc.) | Non-Asbestos Components                         | Asbestos Content              | Comments                                  |
|---------------------------------|------------------------|---------------------------|-------------------------------------------------|-------------------------------|-------------------------------------------|
| A-D (Bag)<br>130 Liberty Street | 3030823                | Floor A<br>Grid D         | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 40.00 %<br>45.25 %<br>14.75 % | None detected<br>Gray Fibrous Debris      |
| 1-B (Bag)<br>130 Liberty Street | 3030824                | Floor 1<br>Grid B         | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 81.50 %<br>14.75 %<br>3.75 %  | None detected<br>Dark Gray Fibrous Debris |
| 1-F (Bag)<br>130 Liberty Street | 3030826                | Floor 1<br>Grid F         | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 63.00 %<br>32.00 %<br>5.00 %  | None detected<br>White Fibrous Debris     |
| 2-B (Bag)<br>130 Liberty Street | 3030829                | Floor 2<br>Grid B         | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 64.25 %<br>20.25 %<br>7.25 %  | Chrysotile 0.25%<br>White Fibrous Debris  |
| 3-C (Bag)<br>130 Liberty Street | 3030834                | Floor 3<br>Grid C         | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 73.25 %<br>20.00 %<br>6.50 %  | Chrysotile 0.25%<br>White Fibrous Debris  |
| 4-E (Bag)<br>130 Liberty Street | 3030838                | Floor 4<br>Grid E         | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 63.25 %<br>29.50 %<br>7.00 %  | Chrysotile 0.25%<br>White Fibrous Debris  |
| 5-D (Bag)<br>130 Liberty Street | 3030844                | Floor 5<br>Grid D         | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 75.25 %<br>18.00 %<br>6.75 %  | None detected<br>White Fibrous Debris     |
| 7-H (Bag)<br>130 Liberty Street | 3030849                | Floor 7<br>Grid H         | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 49.75 %<br>40.50 %<br>9.50 %  | Chrysotile 0.25%<br>White Fibrous Debris  |

RJ LeeGroup, Inc.  
 350 Hochberg Road  
 Monroeville, PA 15146

**Polarized Light Microscopy (PLM) Results, EPA/600/R-93/116 (NYS ELAP 198.1) Point Count Method**  
**RJ Lee Group Project No. LSH204785**

Analyst: WHP

**Analysis Report for Gash Emergency Samples collected 06/05/02**

| Sample ID                                    | RJ Lee Group Sample ID | Building/location (desc.) | Non-Asbestos Components                         |                               | Asbestos Content | Comments             |
|----------------------------------------------|------------------------|---------------------------|-------------------------------------------------|-------------------------------|------------------|----------------------|
| 8-G (2 bags received)<br>130 Liberty Street  | 3030851                | Floor 8<br>Grid G         | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 60.50 %<br>34.75 %<br>4.25 %  | Chrysotile 0.5%  | White Fibrous Debris |
| 9-G (Bag)<br>130 Liberty Street              | 3030852                | Floor 9<br>Grid G         | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 63.25 %<br>27.50 %<br>8.50 %  | Chrysotile 0.75% | White Fibrous Debris |
| 10-D (Bag)<br>130 Liberty Street             | 3030853                | Floor 10<br>Grid D        | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 59.00 %<br>37.25 %<br>3.75 %  | None detected    | White Fibrous Debris |
| 11-B (3 bags received)<br>130 Liberty Street | 3030854                | Floor 11<br>Grid B        | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 73.50 %<br>20.00 %<br>6.50 %  | Amosite < 0.25%  | Gray Fibrous Debris  |
| 12-D (Bag)<br>130 Liberty Street             | 3030857                | Floor 12<br>Grid D        | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 55.75 %<br>36.25 %<br>6.75 %  | Chrysotile 1.25% | White Fibrous Debris |
| 15-A (Bag)<br>130 Liberty Street             | 3030863                | Floor 15<br>Grid A        | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 68.00 %<br>25.75 %<br>6.25 %  | None detected    | Gray Fibrous Debris  |
| 17-C (Bag)<br>130 Liberty Street             | 3030859                | Floor 17<br>Grid C        | Non-fibrous mat'l<br>Cellulose<br>Fibrous Glass | 67.25 %<br>22.50 %<br>10.25 % | None detected    | White Fibrous Debris |
| 17-F (Bag)<br>130 Liberty Street             | 3030860                | Floor 17<br>Grid F        | Non-fibrous mat'l<br>Fibrous Glass<br>Cellulose | 63.00 %<br>26.50 %<br>10.50 % | None detected    | Gray Fibrous Debris  |

RJ Lee Group, Inc.  
350 Hochberg Road  
Monroeville, PA 15146

Page 2 of 2

**Polarized Light Microscopy (PLM) Results, EPA/600/R-93/116 (NYS ELAP 198.1) Point Count Method**  
**RJ Lee Group Project No. LSH204785**

Analyst: WHP

**Analysis Report for Gash Emergency Samples collected 06/05/02**

| Sample ID                        | RJ Lee Group Sample ID | Building/location (desc.) | Non-Asbestos Components |         | Asbestos Content | Comments             |
|----------------------------------|------------------------|---------------------------|-------------------------|---------|------------------|----------------------|
| 18-A (Bag)<br>130 Liberty Street | 3030867                | Floor 18<br>Grid A        | Non-fibrous mat'l       | 72.75 % | Chrysotile 0.25% | Gray Fibrous Debris  |
|                                  |                        |                           | Fibrous Glass           | 24.00 % |                  |                      |
|                                  |                        |                           | Cellulose               | 3.60 %  |                  |                      |
| 19-F (Bag)<br>130 Liberty Street | 3030866                | Floor 19<br>Grid F        | Non-fibrous mat'l       | 62.00 % | Amosite < 0.25%  | Gray Fibrous Debris  |
|                                  |                        |                           | Fibrous Glass           | 26.50 % |                  |                      |
|                                  |                        |                           | Cellulose               | 11.25 % |                  |                      |
| 20-F (Bag)<br>130 Liberty Street | 3030876                | Floor 20<br>Grid F        | Non-fibrous mat'l       | 87.25 % | None detected    | Gray Fibrous Debris  |
|                                  |                        |                           | Fibrous Glass           | 21.25 % |                  |                      |
|                                  |                        |                           | Cellulose               | 11.50 % |                  |                      |
| 21-D (Bag)<br>130 Liberty Street | 3030872                | Floor 21<br>Grid D        | Non-fibrous mat'l       | 82.25 % | None detected    | White Fibrous Debris |
|                                  |                        |                           | Cellulose               | 12.25 % |                  |                      |
|                                  |                        |                           | Fibrous Glass           | 5.50 %  |                  |                      |
| 22-F (Bag)<br>130 Liberty Street | 3030881                | Floor 22<br>Grid F        | Non-fibrous mat'l       | 65.25 % | None detected    | Gray Fibrous Debris  |
|                                  |                        |                           | Fibrous Glass           | 22.75 % |                  |                      |
|                                  |                        |                           | Cellulose               | 12.00 % |                  |                      |
| 23-A (Bag)<br>130 Liberty Street | 3030887                | Floor 23<br>Grid A        | Non-fibrous mat'l       | 78.00 % | None detected    | Gray Fibrous Debris  |
|                                  |                        |                           | Fibrous Glass           | 15.50 % |                  |                      |
|                                  |                        |                           | Cellulose               | 6.50 %  |                  |                      |
| 24-H (Bag)<br>130 Liberty Street | 3030886                | Floor 24<br>Grid H        | Non-fibrous mat'l       | 69.25 % | None detected    | Gray Fibrous Debris  |
|                                  |                        |                           | Fibrous Glass           | 28.00 % |                  |                      |
|                                  |                        |                           | Cellulose               | 2.75 %  |                  |                      |

RJ LeeGroup, Inc.  
 150 Hochberg Road  
 Monaca, PA 15106