

EMSL Analytical, Inc.

307 West 38th Street, New York, NY 10018

Phone: 212-290-0051 Fax: 212-290-0058 Email: manhattanlab@emsl.com

EMSL

Attn: TRC Environmental Consultants
1430 Broadway
10th Floor
New York, NY 10018

Fax: (212) 221-7840 Phone: 212-221-7822

Project: 35052-0000-00015/ New York City Law Department/ 40
Worth St.

Customer ID: TRCE51
Customer PO:
Received: 12/12/02 4:01 PM


EMSL Order: 030217957
EMSL Project ID:
Analysis Date: 12/16/2002

Asbestos Analysis via Transmission Electron Microscopy ASTM Method D5755-95

SAMPLE ID	AREA SAMPLED (cm ²)	ASBESTOS TYPE	ASBESTOS STRUCTURES	Sensitivity (str/cm ²)	CONCENTRATION (str/cm ²)	COMMENTS
MS121202MV40 1 030217957-0001	100	None Detected	<4	398.911	<1595.650	
MS121202MV40 2 030217957-0002	100	None Detected	<4	531.882	<2127.530	
MS121202MV40 3 030217957-0003	100	Chrysotile	12	398.911	4786.940	
MS121202MV40 4 030217957-0004	100	Chrysotile	103	1329.700	136960.000	
MS121202MV40 5 030217957-0005	100	Chrysotile	16	398.911	6382.580	
MS121202MV40 6 030217957-0006	100	Chrysotile	5	7978.230	39891.100	
MS121202MV40 7 030217957-0007	100	Chrysotile	8	997.278	7978.230	
MS121202MV40 8 030217957-0008	100	Chrysotile	103	1329.700	136960.000	
MS121202MV40 9 030217957-0009	100	Chrysotile	49	398.911	19546.700	

Ghayath Elias

Analyst



Laboratory Manager
or other approved signatory

The above report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical, Inc.

TEMMicro-1

1

EMSL Analytical, Inc.

17 West 38th Street, New York, NY 10018

Phone: 212-290-0051 Fax: 2122900058 Email: manhattanlab@emsl.com

EMSL

ttn: TRC Environmental Consultants
 1430 Broadway
 10th Floor
 New York, NY 10018
 Phone: 212-221-7822
 (212) 221-7840
 Project: 35052-0000-00015/ New York City Law Department/ 40 Worth St.


Customer ID: TRCE51
 Customer PO:
 Received: 12/12/02 4:01 PM
 EMSL Order: 030217957
 EMSL Project ID:
 Analysis Date: 12/16/02

Asbestos Analysis via Transmission Electron Microscopy ASTM Method D5755-95

PLE ID	AREA SAMPLED (cm ²)	ASBESTOS TYPE	ASBESTOS STRUCTURES	Sensitivity (str/cm ²)	CONCENTRATION (str/cm ²)	COMMENTS
21202MV41 957-0010	100	Chrysotile	8	398.911	3191.290	
21202MV41 957-0011	100	Chrysotile	64	797.823	51060.600	
21202MVFB 957-0012	0	Chrysotile	<4			Asbestos detected at levels below the detection limit.

yath Elias

/st



 Laboratory Manager
 or other approved signatory

above report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical, Inc.

EMMicro-1

2

CITY_21MC100_004879547