NYC 9/11 Public Portal Document


# ATC Associates

104 East 25 Street, New York, NY 10010

Phone: (212) 353-8280 Fax: (212) 353-8306


**Attn:** Mr. Bernard Orlan
N.Y.C. Board of Education
28-11 Queens Plaza North
Long Island City, NY 11101

**Fax:** (212) 475-4122 **Phone:** (212) 477-8941

**Project:** H.S. Of Economics And Finance

**Received:** 5/31/02 9:00:00 PM
**ATC Group #:** 7922
**Analysis Date:** 6/1/02

## Asbestos Fiber Analysis by Transmission Electron Microscopy (TEM) Performed by EPA 40 CFR Part 763 Final Rule (AHERA)

| *Sample* | *Volume* | *Area Analyzed* | *Non Asb* | *Asbestos Type(s)* | *# Structures 0.5μ-5* | *5μ* | *Analytical Sensitivity (S/cc)* | *Asbestos Concentration (S/mm²)* | *(S/cc)* | *Notes* |
|---|---|---|---|---|---|---|---|---|---|---|
| 03 *7922 -1* | 1896.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0045 | <22.24 | <0.0045 | |
| 04 *7922 -2* | 1904.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0045 | <22.24 | <0.0045 | |
| 05 *7922 -3* | 1904.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0045 | <22.24 | <0.0045 | |
| 06 *7922 -4* | 1912.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0045 | <22.24 | <0.0045 | |
| 07 *7922 -5* | 1920.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0045 | <22.24 | <0.0045 | |
| 08 *7922 -6* | 1944.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0044 | <22.24 | <0.0044 | |
| 09 *7922 -7* | 1848.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0046 | <22.24 | <0.0046 | |

MARK PEYSAKHOV
Analyzed by:

MICHAEL A. GORYCKI, Ph.D.
Approved by:

Disclaimer: The laboratory is not responsible for data reported in structures/cc, which is dependent on volume collected by non-laboratory personnel. This lab is only responsible for data reported in structures/mm². This report may not be reproduced, except in full, without written approval by ATC Associates Inc. This report may not be used to claim product endorsement by NVLAP or any other agency of the U.S. Government. This reports relates only to the samples reported above. Quality control data (including 95% confidence limits and laboratory and analysis' accuracy and precision) is available upon request.

Accredited for NVLAP PLM/TEM #101187-0, NY State ELAP #10879



CONFIDENTIAL, CITY_21MC100_003461207

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

NYC-WTC_000258463

NYC 9/11 Public Portal Document

**Attn:** Mr. Bernard Orlan
N.Y.C. Board of Education
28-11 Queens Plaza North
Long Island City, NY 11101
**Fax:** (212) 475-4122 **Phone:** (212) 477-8941
**Project:** H.S. Of Economics And Finance

**Received:** 5/31/02 9:00:00 PM
**ATC Group #:** 7922
**Analysis Date:** 6/1/02

## Asbestos Fiber Analysis by Transmission Electron Microscopy (TEM) Performed by EPA 40 CFR Part 763 Final Rule (AHERA)

| Sample | Volume | Area Analyzed | Non Asb | Asbestos Type(s) | # Structures 0.5μ-5 | # Structures 5μ | Analytical Sensitivity (S/cc) | Asbestos Concentration (S/mm²) | Asbestos Concentration (S/cc) | Notes |
|---|---|---|---|---|---|---|---|---|---|---|
| 10 *7922 -8* | 1840.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0047 | <22.24 | <0.0047 | |
| 11 *7922 -9* | 1816.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0047 | <22.24 | <0.0047 | |
| 12 *7922 -10* | 1824.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0047 | <22.24 | <0.0047 | |
| 13 *7922 -11* | 1808.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0047 | <22.24 | <0.0047 | |
| 14 *7922 -12* | 1808.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0047 | <22.24 | <0.0047 | |
| 15 *7922 -13* | 1808.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0047 | <22.24 | <0.0047 | |
| 16 *7922 -14* | 1816.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0047 | <22.24 | <0.0047 | |
| 17 *7922 -15* | 1808.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0047 | <22.24 | <0.0047 | |
| 18 *7922 -16* | 1816.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0047 | <22.24 | <0.0047 | |

MARK PEYSAKHOV
Analyzed by:

MICHAEL A. GORYCKI, Ph.D.
Approved by:

Disclaimer: The laboratory is not responsible for data reported in structures/cc, which is dependent on volume collected by non-laboratory personnel. This lab is only responsible for data reported in structures/mm². This report may not be reproduced, except in full, without written approval by ATC Associates Inc. This report may not be used to claim product endorsement by NVLAP or any other agency of the U.S. Government. This reports relates only to the samples reported above. Quality control data (including 95% confidence limits and laboratory and analysis' accuracy and precision) is available upon request.

Accredited for NVLAP PLM/TEM #101187-0, NY State ELAP #10879



CONFIDENTIAL, CITY_21MC100_003461208
SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

NYC-WTC_000258464

NYC 9/11 Public Portal Document

**Attn:** Mr. Bernard Orlan
N.Y.C. Board of Education
28-11 Queens Plaza North
Long Island City, NY 11101
**Fax:** (212) 475-4122 **Phone:** (212) 477-8941

**Project:** H.S. Of Economics And Finance

**Received:** 5/31/02 9:00:00 PM
**ATC Group #:** 7922
**Analysis Date:** 6/1/02

## Asbestos Fiber Analysis by Transmission Electron Microscopy (TEM) Performed by EPA 40 CFR Part 763 Final Rule (AHERA)

| *Sample* | *Volume* | *Area Analyzed* | *Non Asb* | *Asbestos Type(s)* | *# Structures 0.5μ-5* | *5μ* | *Analytical Sensitivity (S/cc)* | *Asbestos Concentration (S/mm²)* | *(S/cc)* | *Notes* |
|---|---|---|---|---|---|---|---|---|---|---|
| 19 *7922 -17* | 1856.00 | 0.0450 | 0 | None Detected | 0 | 0 | 0.0046 | <22.24 | <0.0046 | |

MARK PEYSAKHOV
Analyzed by:

MICHAEL A. GORYCKI, Ph.D.
Approved by:

Disclaimer: The laboratory is not responsible for data reported in structures/cc, which is dependent on volume collected by non-laboratory personnel. This lab is only responsible for data reported in structures/mm². This report may not be reproduced, except in full, without written approval by ATC Associates Inc. This report may not be used to claim product endorsement by NVLAP or any other agency of the U.S. Government. This reports relates only to the samples reported above. Quality control data (including 95% confidence limits and laboratory and analysis' accuracy and precision) is available upon request.

Accredited for NVLAP PLM/TEM #101187-0, NY State ELAP #10879



CONFIDENTIAL, CITY_21MC100_003461209
SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

NYC-WTC_000258465

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1896 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 1 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 03 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | 18 F | **Magnification:** | 20,000 |
| **GRID ID:** | 2 A O | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO No | GO Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 20 | 1 G3 | 1-S20 | | | | | | | | | | | |
| — | 2 C13 | — | | | | | | | | | | | |
| 20 | 3 C1 | — | | | | | | | | | | | |
| | 4 H1 | — | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance:
<50% undissolved filter, overlapped or folded
<10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

**Totals**

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1904 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 2 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 04 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | 1185 | **Magnification:** | 20,000 |
| **GRID ID:** | 29S | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. No | GO. Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | Length >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 | 1C2 | NSD | | | | | | | | | | | |
| 2 | 1P2 | — | | | | | | | | | | | |
| 3 | 1011 | — | | | | | | | | | | | |
| 4 | 851 | — | | | | | | | | | | | |

29 — 25

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance:
<50% undissolved filter, overlapped or folded
<10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

## Totals

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | — | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1904 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 3 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 05 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | H E F | **Magnification:** | 20,000 |
| **GRID ID:** | J C W | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. | | Structure No | Structure Type | | | | Length | | ID of Structure N or √ | | | | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| No | Coord | | F | B | C | M | >=05 µ <5µ | >=5µ | Chrys | Amphibole | Nonasb | Ambig/ND | |
| 1 | X 7 | NSD | | | | | | | | | | | |
| JC 2 | R7 | — C | | | | | | | | | | | |
| 3 | Q2 | — C | | | | | | | | | | | |
| JC 4 | X2 | — C | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber

B = Bundle (<3 fibers <1 fiber diameter apart

C = Cluster (>3 Intersections)

M = Matrix

NSD = No Structures Detected

Grid acceptance:

<50% undissolved filter, overlapped or folded <10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

## Totals

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | - | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

NYC 9/11 Public Portal Document

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1912 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 4 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 06 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | 46 | **Magnification:** | 20,000 |
| **GRID ID:** | 3 | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. No | GO. Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | Length >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 | A7 | NSD | | | | | | | | | | | |
| 2 | 20 | — | | | | | | | | | | | |
| 3 | 07 | — | | | | | | | | | | | |
| 4 | 21 | — | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber

B = Bundle (<3 fibers <1 fiber diameter apart

C = Cluster (>3 Intersections)

M = Matrix

NSD = No Structures Detected

Grid acceptance:

<50% undissolved filter, overlapped or folded <10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

**Totals**

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1920 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 5 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 07 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | H66 | **Magnification:** | 20,000 |
| **GRID ID:** | JFEC | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. No Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 D7 | 1050 | | | | | | | | | | | |
| 2 E7 | — | | | | | | | | | | | |
| 3 H1 | — | | | | | | | | | | | |
| 4 H4 | — | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance:
<50% undissolved filter, overlapped or folded
<10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

**Totals**

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | - | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1944 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 6 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 08 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | 1186 | **Magnification:** | 20,000 |
| **GRID ID:** | Euro | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. No | GO. Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | Length >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 | E8 | NSD | | | | | | | | | | | |
| 2 | J8 | — | | | | | | | | | | | |
| 3 | K1 | — | | | | | | | | | | | |
| 4 | K1 | — | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance:
<50% undissolved filter, overlapped or folded
<10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

| AMPHIBOLES |
|---|
| Amosite |
| Crocidolite |
| Anthophyllite |
| Tremolite |
| Actinolite |

**Totals**

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | - | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

NYC 9/11 Public Portal Document

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1848 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 7 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 09 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | 11.8G | **Magnification:** | 20,000 |
| **GRID ID:** | L9S | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. No Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 E1 | NSD | | | | | | | | | | | |
| 2 J1 | —C | | | | | | | | | | | |
| 3 D1 | —C | | | | | | | | | | | |
| 4 C1 | —C | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance:
<50% undissolved filter, overlapped or folded
<10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

**Totals**

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1840 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 8 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 10 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | 118 a | **Magnification:** | 20,000 |
| **GRID ID:** | 5 C1 c | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. No | GO. Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 5 C | 1 R1 | NSD | | | | | | | | | | | |
| | 2 K1 | — | | | | | | | | | | | |
| 5 C | 3 J2 | — | | | | | | | | | | | |
| | 4 Q2 | — | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance:
<50% undissolved filter, overlapped or folded
<10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

**Totals**

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | -- | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

NYC 9/11 Public Portal Document

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1816 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 9 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 11 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | 1165 | **Magnification:** | 20,000 |
| **GRID ID:** | 5 PK | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. No | GO. Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 | L2 | NSD | | | | | | | | | | | |
| 2 | P2 | — | | | | | | | | | | | |
| 3 | Q3 | — | | | | | | | | | | | |
| 4 | M3 | — | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance:

<50% undissolved filter, overlapped or folded <10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
*Crocidolite*
Anthophyllite
Tremolite
Actinolite

**Totals**

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |



SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

NYC-WTC_000258474

NYC 9/11 Public Portal Document

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1824 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 10 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 12 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | 11 B C | **Magnification:** | 20,000 |
| **GRID ID:** | 5-7 B 11 | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO | | Structure No | Structure Type | | | | Length | | ID of Structure N or √ | | | | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| No | Coord | | F | B | C | M | >=05 µ <5µ | >=5µ | Chrys | Amphibole | Nonasb | Ambig/ND | |
| 5 F | 1 D1 | NSD | | | | | | | | | | | |
| — | 2 E1 | — " | | | | | | | | | | | |
| | 3 C1 | — " | | | | | | | | | | | |
| 6 A | 4 A3 | — " | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber

B = Bundle (<3 fibers <1 fiber diameter apart

C = Cluster (>3 Intersections)

M = Matrix

NSD = No Structures Detected

Grid acceptance:

<50% undissolved filter, overlapped or folded <10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

## Totals

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | - | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1808 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 11 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 13 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | 1165 | **Magnification:** | 20,000 |
| **GRID ID:** | 6mo | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MC

MARK PEYSAKHOV

| GO. No | Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | 1 C/ | NSD | | | | | | | | | | | |
| 6 cr | 2 M1 | — | | | | | | | | | | | |
| — | 3 M7 | — | | | | | | | | | | | |
| 60 | 4 D7 | — | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber

B = Bundle (<3 fibers <1 fiber diameter apart

C = Cluster (>3 Intersections)

M = Matrix

NSD = No Structures Detected

Grid acceptance:

<50% undissolved filter, overlapped or folded <10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

## Totals

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | - | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

NYC 9/11 Public Portal Document

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1808 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 12 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 14 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | HEA | **Magnification:** | 20,000 |
| **GRID ID:** | 6 A S | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. No Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 6A 1 C1 | NSD | | | | | | | | | | | |
| 2 A1 | — | | | | | | | | | | | |
| 3 C1 | — | | | | | | | | | | | |
| 6S 4 C1 | — | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber

B = Bundle (<3 fibers <1 fiber diameter apart

C = Cluster (>3 Intersections)

M = Matrix

NSD = No Structures Detected

Grid acceptance:

<50% undissolved filter, overlapped or folded <10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

## Totals

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | - | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1808 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 13 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 15 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | A B F | **Magnification:** | 20,000 |
| **GRID ID:** | 2 C a | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. | | Structure No | Structure Type | | | | Length | | ID of Structure N or √ | | | | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| No | Coord | | F | B | C | M | >=05 µ <5µ | >=5µ | Chrys | Amphibole | Nonasb | Ambig/ND | |
| 1 | X 9 | NSD | | | | | | | | | | | |
| 2 | R 9 | — C | | | | | | | | | | | |
| 3 | R 1 | — C | | | | | | | | | | | |
| 4 | Y 1 | — C | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance:
<50% undissolved filter, overlapped or folded
<10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

**Totals**

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

NYC 9/11 Public Portal Document

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1816 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 14 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 16 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | HBC | **Magnification:** | 20,000 |
| **GRID ID:** | >MA | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. No | GO. Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 | C1 | NSD | | | | | | | | | | | |
| 2 | S1 | — C | | | | | | | | | | | |
| 3 | K1 | — C | | | | | | | | | | | |
| 4 | C1 | — C | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance:

<50% undissolved filter, overlapped or folded <10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

**Totals**

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | - | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

NYC 9/11 Public Portal Document

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1808 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 15 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 17 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | 1186 | **Magnification:** | 20,000 |
| **GRID ID:** | >F8a | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. No Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 K1 | NSD | | | | | | | | | | | |
| 2 K1 | — c | | | | | | | | | | | |
| 3 E2 | — c | | | | | | | | | | | |
| 4 J2 | — c | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance:
<50% undissolved filter, overlapped or folded
<10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

**Totals**

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

CONFIDENTIAL, CITY_21MC100_003461224

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008

NYC-WTC_000258480

NYC 9/11 Public Portal Document

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1816 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 16 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 18 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | 11 6 E | **Magnification:** | 20,000 |
| **GRID ID:** | B 4 D | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. No | GO. Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | Length >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 8 | C7 | NSD | | | | | | | | | | | |
| — | E 7 | — | | | | | | | | | | | |
| 80 | 3 D1 | — | | | | | | | | | | | |
| | 6 E1 | — | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance:
<50% undissolved filter, overlapped or folded
<10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

**Totals**

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |



NYC-WTC_000258481

# TEM Asbestos (air) Count Sheet

| | | | |
|---|---|---|---|
| **Client Name:** | NYC BOE | **Volume (liters):** | 1856 |
| **Lab Group #:** | 7922 | **Filter Type / Filter Area:** | MCE 385 mm² |
| **Lab Sample #:** | 17 | **Grid Opening Size:** | 0.01124 |
| **Client Sample #:** | 19 | **Area Examined:** | 0.04496 mm² |
| **GRID BOX:** | H8C | **Magnification:** | 20,000 |
| **GRID ID:** | 8 Q S | **Accelerating Voltage:** | 100 KeV |
| **# Grid Openings:** | 4 | **Analysis Date:** | 6/1/02 |

**Analysis Performed By:** MARK PEYSAKHOV

| GO. No | GO. Coord | Structure No | Structure Type F | B | C | M | Length >=05 µ <5µ | Length >=5µ | ID of Structure N or √ Chrys | Amphibole | Nonasb | Ambig/ND | EDS (Nonadb Elements) |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 1 | J3 | NSD | | | | | | | | | | | |
| 2 | Q3 | — | | | | | | | | | | | |
| 3 | K7 | — | | | | | | | | | | | |
| 4 | K7 | — | | | | | | | | | | | |

Struct = > 0.5µ > 5:1 Aspect Ratio

√= Positive diffraction pattern properties conforming to laboratory identification criteria observed

√= EDS spectrum conforming to laboratory identification criteria observed

F = Single Fiber
B = Bundle (<3 fibers <1 fiber diameter apart
C = Cluster (>3 Intersections)
M = Matrix
NSD = No Structures Detected

Grid acceptance:
<50% undissolved filter, overlapped or folded
<10% particulate coverage >50% coverage ate least 20 unfolded or overlapped grid squares <5% holes or opaque areas

AMPHIBOLES
Amosite
Crocidolite
Anthophyllite
Tremolite
Actinolite

## Totals

| | F | B | C | M | >5µ |
|---|---|---|---|---|---|
| Chrysotile | — | | | | |
| Amphibole | | | | | |
| Ambiguous | | | | | |
| Non-Asbestos | | | | | |
| Non-Identified | | | | | |

NYC-WTC_000258483

NYC 9/11 Public Portal Document

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008 CONFIDENTIAL,

CITY_21MC100_00346122

ATC ASSOCIATES INC.

# AIR MONITORING DATA AND CHAIN OF CUSTODY FORM

7922



**TURNAROUND TIME**

☐ 2 hrs ☐ 6 hrs ☐ 48 hrs ☐ Standard
☐ 4 hrs ☐ 24 hrs ☐ 72 hrs ☐ Other ASAP

7922 17/20 92134-92153

## PROJECT INFORMATION

| 1. Client: | 2. Project Name | 3. Project # | 4. Project Monitor: | 4c. Rotameter Number: |
|---|---|---|---|---|
| NYC/B.O.E. | H.S. FOR FINANCE/ECONOMICS | 14584-865 | — | HP-38 |
| | 2a. Project Address 100 TRINITY PLACE, NYC. | 3a. Task # | 4a. Air Sampler: M. G. KHAN | |

| 5. Date: | 6. Abatement Location: | 7. ☐ PCM (0.8 micron MCE) | 8. ☒ TEM (0.45 micron MCE) | 9. Type: | | |
|---|---|---|---|---|---|---|
| 5/31/02 | AS PER PROTOCOL | Cassette/Filter Manufacture N/A. | Cassette/Filter Manufacture Multi-Metrics | a. ☐ Background | c. ☐ Abatement | f. ☐ Environmental |
| | | Lot # - | Lot # 01205916 | b. ☐ Pre-Abate | d. ☐ Post-Abate | g. ☒ ~~Ambient~~ |
| | | | | | e. ☐ OSHA | h. ☐ Other |

## DAILY AIR SAMPLE RECORD

| 10. Sample I.D. Number | 11. Pump Number | 12. Sample Location 12a. IWA | 12b. OWA | 12c. Sample Coordinates | 13. Time (24 hrs clock) 13a. Start | 13b. End | 13c. Total | 14. Flow Rate (L/min.) 14a. Start | 14b. End | 14b. Avg | 15. Total Air Vol. (liters) | 16. # Fibers/Fields Minus Blank | 17. Fiber Conc. F/CC |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Ø1 | | | | Field Blank | | | | | | | | | |
| Ø2 | | | | Field Blank | | | | | | | | | |
| Ø3 | | | | OUTSIDE BLDG. BY THE MAIN ENTRANCE. | 0732 | 1129 | 237 | 8.0 | 8.0 | 8.0 | 1896 | | |
| Ø4 | | | | 1st FLOOR LOBBY O/SIDE AUDITORIUM. | 0733 | 1131 | 238 | 8.0 | 8.0 | 8.0 | 1904 | | |
| Ø5 | | | | INSIDE AUDITORIUM AT FIRST FLOOR. | 0735 | 1133 | 238 | 8.0 | 8.0 | 8.0 | 1904 | | |
| Ø6 | | | | STAIRCASE "B" OPEN AREA AT 7th FLOOR. | 0737 | 1136 | 239 | 8.0 | 8.0 | 8.0 | 1912 | | |
| Ø7 | | | | CAFETERIA — N/E AT 8th FLOOR. | 0739 | 1139 | 240 | 8.0 | 8.0 | 8.0 | 1920 | | |
| Ø8 | | | | UP AT THE TOP OF THE ROOF. | 0743 | 1146 | 243 | 8.0 | 8.0 | 8.0 | 1944 | | |

## CHAIN OF CUSTODY

| | 18. Relinquished By: | 19. Received By: | 20. Date: | 21. Time: |
|---|---|---|---|---|
| I | M. G. Khan. | M. Gray | 5/3/02 | 21:00 |
| II | | | | |
| III | | | | |

## LAB INFORMATION (ATC ELAP # 10879, ATC NVLAP # 1187)

| 22. Lab Name: | 23. Date: | 24. Time: |
|---|---|---|
| a. Analyzed By: | 6/1 | 1100 |
| b. QC By: | | |
| c. Lab Batch #: | | |

25. Microscope Make/Serial #:
☐ Nikon Labophot 238913
☐ Nikon Labophot 238917
☐ Nikon Labophot 239079

Analysis Methodology
PCM - NIOSH 7400A
TEM - AHERA

26. ATC Project Manager: MARK TERJESEN

27. Result To: YIANNIS EFSTATHIOU
~~Beeper~~/Phone #'s 646-772-1155

28. Comments: Please call the Project Manager with result.

WHITE - File YELLOW - Client/Report PINK - Lab GOLDENROD - Field

NY-1 (1/01)

NYC-WTC_000258484

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008 CONFIDENTIAL,

CITY_21MC100_003461228

NYC 9/11 Public Portal Document

# AIR MONITORING DATA AND CHAIN OF CUSTODY FORM

7922



**TURNAROUND TIME**

☐ 2 hrs ☐ 6 hrs ☐ 48 hrs ☐ Standard
☐ 4 hrs ☐ 24 hrs ☐ 72 hrs ☐ Other ASAP

## PROJECT INFORMATION

| 1. Client: | 2. Project Name | 3. Project # | 4. Project Monitor: | 4c. Rotameter Number: |
|---|---|---|---|---|
| NYC/BOE | H.S. FOR FINANCE/ECONOMICS | 14584-865 | — | HP-38 |
| | 2a. Project Address: 100 TRINITY PLACE NYC | 3a. Task # 01 | 4a. Air Sampler: M.G. Khan | |

| 5. Date: | 6. Abatement Location: | 7. ☐ PCM (0.8 micron MCE) | 8. ☑ TEM (0.45 micron MCE) | 9. Type: | | |
|---|---|---|---|---|---|---|
| 5/31/02 | AS PER PROTOCOL | Cassette/Filter Manufacture N/A. Lot # | Cassette/Filter Manufacture Multi-Metrics Lot # 01205916 | a. ☐ Background b. ☐ Pre-Abate | c. ☐ Abatement d. ☐ Post-Abate e. ☐ OSHA | f. ☐ Environmental g. ☑ Ambient h. ☐ Other |

## DAILY AIR SAMPLE RECORD

| 10. Sample I.D. Number | 11. Pump Number | 12. Sample Location 12a. IWA | 12b. OWA | 12c. Sample Coordinates | 13. Time (24 hrs clock) 13a. Start | 13b. End | 13c. Total | 14. Flow Rate (L/min.) 14a. Start | 14b. End | 14b. Avg | 15. Total Air Vol. (liters) | 16. # Fibers/Fields Minus Blank | 17. Fiber Conc. F/CC |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | Field Blank | | | | | | | | | |
| | | | | Field Blank | | | | | | | | | |
| 09 | | | | OUTSIDE BLDG. BY THE MAIN ENTRANCE | 1129 | 1520 | 231 | 8.0 | 8.0 | 8.0 | 1848 | | |
| 10 | | | | 1ST FLOOR LOBBY O/SIDE AUDITORIUM. | 1131 | 1521 | 230 | 8.0 | 8.0 | 8.0 | 1840 | | |
| 11 | | | | STAIRCASE "B" OPEN AREA AT 7TH FLOOR. | 1136 | 1523 | 227 | 8.0 | 8.0 | 8.0 | 1816 | | |
| 12 | | | | UP AT THE TOP OF THE ROOF. | 1146 | 1534 | 228 | 8.0 | 8.0 | 8.0 | 1824 | | |
| 13 | | | | MAIN FLOOR HALLWAY AT 9TH FLOOR | 1538 | 1924 | 226 | 8.0 | 8.0 | 8.0 | 1808 | | |
| 14 | | | | BET. RM 801 AND CAFE-ERIA @ 8TH FLOOR | 1540 | 1926 | 226 | 8.0 | 8.0 | 8.0 | 1808 | | |

## CHAIN OF CUSTODY

| | 18. Relinquished By: | 19. Received By: | 20. Date: | 21. Time: |
|---|---|---|---|---|
| I | M.G. Khan | H. Cruz | 5/31/02 | 21:00 |
| II | — | | | |
| III | | | | |

## LAB INFORMATION (ATC ELAP # 10879, ATC NVLAP # 1187)

| 22. Lab Name: TEA | 23. Date: | 24. Time: |
|---|---|---|
| a. Analyzed By: | 6/1 | 1:00 |
| b. QC By: | | |
| c. Lab Batch #: | | |

25. Microscope Make/Serial #:
☐ Nikon Labophot 238913
☐ Nikon Labophot 238917
☐ Nikon Labophot 239079

Analysis Methodology
PCM - NIOSH 7400A
(TEM - AHERA)

| 26. ATC Project Manager: | 27. Result To: | 28. Comments: |
|---|---|---|
| MARK TERJESEN | YIANNIS EFSTATHIOU<br>Beeper/Phone #'s 646-772-1155 | See page 1 of 3 |

WHITE - File YELLOW - Client/Report PINK - Lab GOLDENROD - Field

NY-1 (1/01)

NYC-WTC_000258485

SUBJECT TO PROTECTIVE ORDER NO. 2, SEPT. 2008 CONFIDENTIAL,

CITY_21MC100_003461229

NYC 9/11 Public Portal Document

ATC ASSOCIATES INC.

# AIR MONITORING DATA AND CHAIN OF CUSTODY FORM

7922



**TURNAROUND TIME**

☐ 2 hrs ☐ 6 hrs ☐ 48 hrs ☐ Standard
☐ 4 hrs ☐ 24 hrs ☐ 72 hrs ☐ Other ASAP

## PROJECT INFORMATION

| 1. Client: | 2. Project Name | 3. Project # | 4. Project Monitor: | 4c. Rotameter Number: |
|---|---|---|---|---|
| NYC/B.O.E. | H.S. FOR FINANCE/ECONOMICS | 14584-865 | | HP-38 |
| | 2a. Project Address: 100 TRINITY PLACE | 3a. Task # 01 | 4a. Air Sampler: M. G. KHAN | |

| 5. Date: | 6. Abatement Location: | 7. ☐ PCM (0.8 micron MCE) | 8. ☒ TEM (0.45 micron MCE) | 9. Type: | | |
|---|---|---|---|---|---|---|
| 5/31/02 | As Per Protocol | Cassette/Filter Manufacture N/A. Lot # | Cassette/Filter Manufacture Multi-Metrics Lot # 01205916 | a. ☐ Background b. ☐ Pre-Abate | c. ☐ Abatement d. ☐ Post-Abate e. ☐ OSHA | f. ☐ Environmental g. ☐ Ambient h. ☐ Other |

## DAILY AIR SAMPLE RECORD

| 10. Sample I.D. Number | 11. Pump Number | 12. Sample Location 12a. IWA | 12b. OWA | 12c. Sample Coordinates | 13. Time (24 hrs clock) 13a. Start | 13b. End | 13c. Total | 14. Flow Rate (L/min.) 14a. Start | 14b. End | 14b. Avg | 15. Total Air Vol. (liters) | 16. # Fibers/Fields Minus Blank | 17. Fiber Conc. F/CC |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | Field Blank | | | | | | | | | |
| | | | | Field Blank | | | | | | | | | |
| 15 | | | | MAIN FLOOR HALLWAY AT 7th FLOOR. | 1542 | 1928 | 226 | 8.0 | 8.0 | 8.0 | 1808 | | |
| 16 | | | | INSIDE CLASS Rm. 608 AT 6th FLOOR | 1544 | 1931 | 227 | 8.0 | 8.0 | 8.0 | 1816 | | |
| 17 | | | | MAIN FLOOR HALLWAY AT 5th FLOOR. | 1547 | 1933 | 226 | 8.0 | 8.0 | 8.0 | 1808 | | |
| 18 | | | | INSIDE CLASS Rm. 406 AT 4th FLOOR. | 1549 | 1936 | 227 | 8.0 | 8.0 | 8.0 | 1816 | | |
| 19 | | | | MAIN FLOOR HALLWAY AT 3RD FLOOR. | 1552 | 1944 | 232 | 8.0 | 8.0 | 8.0 | 1856 | | |
| 20 | | | | SEALED BLANK | | | | | | | | | |

## CHAIN OF CUSTODY

| | 18. Relinquished By: | 19. Received By: | 20. Date: | 21. Time: |
|---|---|---|---|---|
| I | M. G. Khan | H. Ghosh | 5/31/02 | 21:00 |
| II | | | | |
| III | | | | |

## LAB INFORMATION (ATC ELAP # 10879, ATC NVLAP # 1187)

| 22. Lab Name: | 23. Date: | 24. Time: |
|---|---|---|
| a. Analyzed By: | | |
| b. QC By: | | |
| c. Lab Batch #: | | |

25. Microscope Make/Serial #:
☐ Nikon Labophot 238913
☐ Nikon Labophot 238917
☐ Nikon Labophot 239079

Analysis Methodology
PCM - NIOSH 7400A
TEM - AHERA

26. ATC Project Manager: MARK TERTESEN

27. Result To: YIANNIS EFSTATHIOU
Beeper/Phone #'s 646-772-1155

28. Comments: See Page 1 of 3

WHITE - File YELLOW - Client/Report PINK - Lab GOLDENROD - Field

NY-1 (1/01)