NYC 9/11 Public Portal Document

AMBIENT LABS, INC.
159 WEST 25TH STREET
NEW YORK, NY 10001

BULK SAMPLE LABORATORY DATA REPORT

PROJECT : 0211512
CLIENT : Lehman Brothers
LOCATION : 1 WFC & 3 WFC
TECHNICIAN : PETE SCHORK

COLLECTED : 10/30/2001
DATE REC'D : 10/31/2001
TIME REC'D : 4:03 PM
ANALYZED : 10/31/2001

BATCH ID : 3409

SIGNED FOR AMBIENT LABS INC. BY:

Tarek Fato

LABORATORY ID NUMBER	FIELD ID NUMBER	SAMPLE COLOR	SAMPLE DESCRIPTION	ASBESTOS PRESENT	PERCENTOF TOTAL ASBESTOS		SAMPLE CONSTIUTENTS	
B2K91577	20-01	Gray	ON THE 20TH FLOOR SEE DRAWING.	YES	2.00 %	(P)	CHRYSOTILE :	2.00 %
							CELLULOSE :	30.00 %
							MINERAL WOOL :	30.00 %
							NON-FIBROUS :	38.00 %
B2K91578	20-02	Gray	ON THE 20TH FLOOR SEE DRAWING.	NAD	0.00 %	(P)	CELLULOSE :	30.00 %
							MINERAL WOOL :	30.00 %
							NON-FIBROUS :	40.00 %
B2K91579	20-03	Gray	ON THE 20TH FLOOR SEE DRAWING.	NAD	0.00 %	(P)	CELLULOSE :	30.00 %
							MINERAL WOOL :	30.00 %
							NON-FIBROUS :	40.00 %
B2K91580	21-01	Gray	ON THE 21TH FLOOR SEE DRAWING.	YES	0.30 %	(P)	CHRYSOTILE :	.30 %
							CELLULOSE :	30.00 %
							MINERAL WOOL :	30.00 %
							NON-FIBROUS :	39.70 %
B2K91581	21-02	Gray	ONTHE 21TH FLOOR SEE DRAWING.	YES	4.00 %	(P)	CHRYSOTILE :	4.00 %
							CELLULOSE :	40.00 %
							MINERAL WOOL :	20.00 %
							NON-FIBROUS :	36.00 %
B2K91582	21-03	Gray	ON THE 21 TH FLOOR SEE DRAWING.	YES	0.80 %	(P)	CHRYSOTILE :	.80 %
							CELLULOSE :	30.00 %
							MINERAL WOOL :	30.00 %
							NON-FIBROUS :	39.20 %

NAD = No Asbestos Detected. Trace < 0.25 %.
(P) Analysis by Polarized Light Microscopy (PLM) NYS ELAP method 198.1 or EPA/600/R-93/116. (T) Analysis by Transmission Electron Microscopy (TEM) NYS ELAP method 198.4. Polarized Light Microscopy is not consistently reliable in detection of asbestos in floor coverings and similar non-friable organically bound materials. Quantitative transmission electron microscopy is currently the only method that can be used to determine if this material can be considered or treated as non-asbestos containing. No reproduction of all or any portion of this report shall occur without written approval of Ambient Labs, Inc. All results disclosed in this report relate only to the items tested.
NVLAP ID # 101618. NYS ELAP ID # 10865. STATE OF CA ELAP ID # 2139.

CITY_21MC100_002840089

NYC-WTC_000389294

NYC 9/11 Public Portal Document

AMBIENT LABS, INC.
159 WEST 25TH STREET
NEW YORK, NY 10001

BULK SAMPLE LABORATORY DATA REPORT

PROJECT : Q211512
CLIENT : AMEX Towers
LOCATION : 3 World Financial Center
TECHNICIAN :

COLLECTED : 11/8/2001
DATE REC'D : 11/9/2001
TIME REC'D : 10:28 AM
ANALYZED : 11/13/2001

BATCH ID : 3439

SIGNED FOR AMBIENT LABS INC. BY:

LABORATORY ID NUMBER	FIELD ID NUMBER	SAMPLE COLOR	SAMPLE DESCRIPTION	ASBESTOS PRESENT	PERCENTOF TOTAL ASBESTOS		SAMPLE CONSTITUTENTS	
B2K91855	20-04-A	GREY	ELEVATOR ENTERANCE FLOOR.	NAD	0.00 %	(P)	CELLULOSE :	60.00 %
							NON-FIBROUS :	40.00 %
B2K91856	20-05-A	GREY	ON THE 3RD FLOOR WINDOW EAST SIDE WINDOWSILL.	YES	0.30 %	(P)	CHRYSOTILE :	.30 %
							CELLULOSE :	40.00 %
							MINERAL WOOL :	30.00 %
							NON-FIBROUS :	29.70 %
B2K91857	20-06-A	GREY	GIORIOS VIAMIS TOP OF DESK.	NAD	0.00 %	(P)	CELLULOSE :	40.00 %
							MINERAL WOOL :	30.00 %
							NON-FIBROUS :	30.00 %
B2K91858	20-07-A	GREY	WILLIAM CHRIST OFFICE TOP OF DESK.	NAD	0.00 %	(P)	CELLULOSE :	20.00 %
							MINERAL WOOL :	40.00 %
							NON-FIBROUS :	40.00 %
B2K91859	20-08-A	GREY	HALLWAY NEAR MICHAEL REID FILES TOP OF DESK.	NAD	0.00 %	(P)	CELLULOSE :	40.00 %
							MINERAL WOOL :	30.00 %
							NON-FIBROUS :	30.00 %
B2K91860	20-09-A	GREY	MICHEAL DEMARCO OFFICE TOP OF DESK.	NAD	0.00 %	(P)	CELLULOSE :	20.00 %
							MINERAL WOOL :	30.00 %
							NON-FIBROUS :	50.00 %
B2K91861	20-10-A	GREY	RAMOND MIKUIICH TOP OF DESK.	YES	0.30 %	(P)	CHRYSOTILE :	.30 %
							CELLULOSE :	30.00 %
							MINERAL WOOL :	30.00 %
							NON-FIBROUS :	39.70 %

NAD = No Asbestos Detected. Trace < 0.25 %.
(P) Analysis by Polarized Light Microscopy (PLM) NYS ELAP method 198.1 or EPA/600/R-93/116. (T) Analysis by Transmission Electron Microscopy (TEM) NYS ELAP method 198.4. Polarized Light Microscopy is not consistently reliable in detection of asbestos in floor coverings and similar non-friable organically bound materials. Quantitative transmission electron microscopy is currently the only method that can be used to determine if this material can be considered or treated as non-asbestos containing. No reproduction of all or any portion of this report shall occur without written approval of Ambient Labs, Inc. All results disclosed in this report relate only to the items tested.
NVLAP ID # 101618. NYS ELAP ID # 10865. STATE OF CA ELAP ID # 2139.

NOV-19-01 MON 11:39 AM AMBIENT GROUP INC FAX NO. 212 768 1540 P. 02

CITY_21MC100_002840090

NYC-WTC_000389295